

SYSTEM DATA SHEET

Sikafloor® MultiDur HS

AVIATION GRADE RESIN COATING SYSTEM ENGINEERED WITH SIKAFLOOR®-264 AT 28 - 38 MILS (0.7 - 0.9 MM)

PRODUCT DESCRIPTION

Sikafloor® MultiDur HS is a monolithic, solid color epoxy floor system with superior chemical resistance specifically designed for aircraft hangars and aviation environments. This system resists typical aviation fluids such as Jet-A and Skydrol. Sikafloor® MultiDur HS typically installed at 28 -38 mils (0.7 - 0.9 mm).

USES

Sikafloor® MultiDur HS may only be used by experienced professionals.

- Aircraft Maintenance Facilities
- Aircraft Hangars


CHARACTERISTICS / ADVANTAGES

- Durable, impermeable and seamless
- Excellent chemical resistance
- High light reflection
- High compressive strength
- Protect substrate from chemical attack
- Provides good resistance to hydraulic fluids such Skydrol & Jet-A
- Optional integral cove, base and curbs

SYSTEM INFORMATION

System Structure

Sikafloor® MultiDur HS ~ 28 - 38 mils (0.7 - 0.9 mm)



Description	Products	Thickness mils
1. Primer	Sikafloor®-161	8 - 10
2. Body Coat	Sikafloor®-264	12 - 16
3. Top Coat	Sikafloor®-340 + Sikafloor® Urethane Pigment Pack	4 - 6
4. Recommended 2 nd Top Coat	Sikafloor®-340 + Sikafloor® Urethane Pigment Pack	4 - 6

Options Description	Products	Thickness mils
Primers	Sikafloor®-1620	12 - 15
	Sikafloor®-165 FS	8 - 10
Top Coats	Sikafloor®-315* + Sikafloor® Urethane Pigment Pack	3 - 4

* Sikafloor®-315 would be an optional top coat for Low VOC

Color	Available in a broad range of standard and custom colors. Please refer to the Standard Color selection Guide and contact Customer Service for custom color availability.
Nominal thickness	28 - 38 mils (0.7 - 0.9 mm)
Minimum thickness	28 mils (0.7 mm)

TECHNICAL INFORMATION

Shore D Hardness	80	ASTM D2240 at 73°F (23°C) and 50% R.H
Abrasion Resistance	27 mg loss (CS-17/1000 rot/1000 g)	ASTM D4060 at 73°F (23°C) and 50% R.H
Tensile Strength	6,745 psi (46 Mpa)	ASTM D638 at 73°F (23°C) and 50% R.H
Tensile Adhesion Strength	>400 psi (2.7 MPa) (100 % concrete failure)	ASTM D4541 at 73°F (23°C) and 50% R.H
Chemical Resistance	Contact Sika Technical Service for specific information.	
Gloss level	90 (at 60 degrees)	ASTM D523 at 73°F (23°C) and 50% R.H
Coefficient of Friction	0.45 Wet / 0.68 Dry	ANSI 326.3 at 73°F (23°C) and 50 % R.H

APPLICATION INFORMATION

Coverage	Description	Products	Approximates Sq.Ft./kit
	1. Primer	Sikafloor®-161	900@8 mils
	2. Base Coat	Sikafloor®-264	600@12 mils
	3. Top Coat	Sikafloor®-340 + Sikafloor® Urethane Pigment Pack	2,200@4 mils 2 quarts per 5 gallon kit
	4. Recommended 2 nd Top Coat	Sikafloor®-340 + Sikafloor® Urethane Pigment Pack	2,200@4 mils 2 quarts per 5 gallon kit
Options			
	Description	Products	Approximates Sq.Ft./kit
	Primers	Sikafloor®-1620	533@12 mils
		Sikafloor®-165 FS	1,000@8 mils
	Top Coats	Sikafloor®-315 + Sikafloor® Urethane Pigment Pack	2,340@4 mils 2 quarts per 5.34 gallon kit
Ambient Air Temperature	Minimum/Maximum 50/85 °F (10/30 °C)		
Substrate Temperature	Minimum/Maximum 50/85 °F (10/30 °C)		

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

ENVIRONMENTAL, HEALTH AND SAFETY

System Data Sheet
Sikafloor® MultiDur HS
April 2024, Version 03.01
020811900000000163

BUILDING TRUST



APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, form oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit a good bond.

Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI - CSP 3-6. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

Primer

Priming for concrete substrate is required. Prime with either Sikafloor®-161, Sikafloor®-1620 or Sikafloor®-165 FS. Allow the primer to cure (varies with temperature and humidity) until tack free before applying subsequent coats.

Ensure that the primer is pore-free, pinhole-free and provides uniform and complete coverage over the entire substrate.

Please refer to the most current and respective Product Data Sheet for further information.

MIXING

Please refer to the individual Product Data Sheets

APPLICATION

Please refer to the individual Product Data Sheets

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



System Data Sheet
Sikafloor® MultiDur HS
April 2024, Version 03.01
020811900000000163

SikafloorMultiDurHS-en-US-(04-2024)-3-1.pdf



PRODUCT DATA SHEET

Sikafloor®-161

VERSATILE EPOXY RESIN FOR PRIMING

PRODUCT DESCRIPTION

Sikafloor®-161 is a two part, epoxy resin used for priming.

USES

Sikafloor®-161 may only be used by experienced professionals.

Sikafloor®-161 is designed as a primer for Sikafloor® epoxy and urethane coatings, as well as for broadcast and troweled systems.

CHARACTERISTICS / ADVANTAGES

- Low VOC
- Excellent penetration and adhesion
- Easy application
- Short recoat times
- Multi-purpose use
- High solids as supplied

PRODUCT INFORMATION

Packaging	Component A: 3.0 US gal. (11.4 L)	Component A: 50 US gal. (189 L) (2 units needed)
	Component B: 1.5 US gal. (5.7 L)	Component B: 50 US gal. (189 L)
	Components A+B: 4.5 US gal. (17 L)	Components A+B: 150 US gal. (568 L)
	(Ready to mix unit)	
Appearance / Color	Gray transparent after mixing	
Shelf Life	2 years in original unopened container under proper storage	
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 40 °F (4 °C) and 90 °F (32 °C).	

TECHNICAL INFORMATION

Shore D Hardness	80 - 85	ASTM D2240 at 73°F (23°C) and 50% R.H
Abrasion Resistance	CS-17/1,000 cycles/1,000 g - 90 mg loss	ASTM D4060 at 73°F (23°C) and 50% R.H
Impact Strength	0.26 ft/lb (0.35 j)	ASTM D2794 at 73°F (23°C) and 50% R.H
Compressive Strength	7,426 psi (51.2 MPa)	ASTM C695 at 73°F (23°C) and 50% R.H
Flexural Strength	<i>Flexural Strength</i> 8,558 psi (59.0 MPa)	ASTM D790 at 73°F (23°C) and 50% R.H
	<i>Flexural Modulus of Elasticity</i> 8.34 x 10 ⁵ psi (5,750 MPa)	ASTM D790 at 73°F (23°C) and 50% R.H
Tensile Strength	4,902 psi (33.8 MPa)	ASTM C638 at 73°F (23°C) and 50% R.H
Tensile Adhesion Strength	> 400 psi (2.7 MPa) (100 % concrete failure)	ASTM D7234 at 73°F (23°C) and 50% R.H
Chemical Resistance	Please consult Sikafloor Technical Services.	
Thermal Resistance	9.0 g/m ² (24 hours)	ASTM E96 at 73°F (23°C) and 50% R.H
Water Absorption	0.14 g/h - m ²	ASTM D570 at 73°F (23°C) and 50% R.H

APPLICATION INFORMATION

Mixing Ratio	2 : 1 by volume			
Coverage	160–266 ft² / US gal (3.9–6.5 m² / L) at 6–10 mils (0.15–0.25 mm) wet film thickness (w.f.t.).			
Pot Life	Material Temperature	Time		
	50 °F (10 °C)	~ 50 minutes		
	68 °F (20 °C)	~ 25 minutes		
	86 °F (30 °C)	~ 15 minutes		
Cure Time	Ambient & Substrate Temperature	Foot traffic	Light traffic	Full cure
	50 °F (10 °C)	~ 24 hours	~ 3 days	~ 10 days
	68 °F (20 °C)	~ 12 hours	~ 2 days	~ 7 days
	86 °F (30 °C)	~ 8 hours	~ 1 day	~ 4 days
Waiting / Recoat Times	Before applying second coat Sikafloor®-161 on Sikafloor®-161 allow:			
	Ambient & Substrate temperature	Minimum	Maximum	
	50 °F (10 °C)	24 hours	36 hours	
	68 °F (20 °C)	8 hours	24 hours	
	86 °F (30 °C)	6 hours	18 hours	
	Before applying Sikafloor Epoxy or Polyurethane on Sikafloor®-161 allow:			
	Ambient & Substrate temperature	Minimum	Maximum	
	50 °F (10 °C)	24 hours	36 hours	
	68 °F (20 °C)	8 hours	24 hours	
	86 °F (30 °C)	6 hours	24 hours	
Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.				

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

Notes on Limitations:

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

Substrate Moisture Content: Moisture content of concrete substrate must be ≤ 4 % by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared

surface according to this product data sheet (preparation to CSP-3 to CSP-4 as per ICRI guidelines). Do not apply to concrete substrate with moisture levels > 4 % mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter. If moisture content of concrete substrate is > 4 % by mass (pbw – part by weight) but < 6% as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor®-1620. If moisture content is ≥ 6%, use Sikafloor® 22 NA or 24 NA PurCem®.

When relative humidity tests for concrete substrate are conducted per ASTM F2170 for project specific requirements, values must be ≤ 85 %. If values are > 85 % but < 96% according to ASTM F2170 use Sikafloor®-1620. If values are ≥ 96%, use Sikafloor® 22 NA or 24 NA PurCem®.

Material Temperature: Precondition material for at least 24 hours between 65 °F to 75 °F (18 °C to 24 °C)

Ambient Temperature: Minimum/Maximum 50/85 °F

(10/30 °C)

Substrate Temperature: Minimum/Maximum 50/85 °F (10/30 °C). Substrate temperature must be at least 5 °F (3 °C) above measured Dew Point. Mixing and Application must adhere to Material, Ambient and Substrate temperatures listed above or a decrease in product workability and slower cure rates will occur.

Ambient Relative Humidity: Maximum ambient humidity 85% (during application and curing)

Dew Point: Beware of condensation!

The substrate must be at least 5°F (3°C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

Mixing: Do not hand mix Sikafloor materials. Mechanically mix only.

Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Use of thinners will void any applicable Sika warranty. Improper mixing procedure or incorrect mixing ratio may result in moisture sensitivity, whitening, slow cure, soft spots, and other defects.

Application: Apply the primer to the prepared substrate using a squeegee and back roll to provide uniform coverage. Ensure that the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate. If necessary, apply an additional coat to ensure the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate.

- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur. Ensure there is no vapor drive at the time of application. Refer to ASTM D4263, may be used for a visual indication of vapor drive.
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings
- Do not apply Sikafloor to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- Any aggregate used with Sikafloor systems must be non-reactive and oven-dried.
- This product is not designed for negative side waterproofing.
- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).
- Beware of air flow and changes in air flow.

Introduction of dust, debris, and particles, etc. may result in surface imperfections and other defects.

- For professional use only by experienced applicators.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be removed to achieve a level surface prior to the application.

Concrete - Should be cleaned and prepared to achieve a laitance-free and contaminant-free, open textured surface by shot blasting or equivalent mechanical means (CSP-3 to CSP-4 as per ICRI guidelines). Sweep and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual dust will help ensure a tenacious bond between the primer and substrate. Whenever “shot-blasting” is utilized, be careful to leave concrete with a uniform texture. “Over-blasting” will result in reduced coverage rates of the primer and/or subsequent topcoats. The “shotblast” pattern may show through the last coat, known as “tracking”. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and at least 218 psi (1.5 MPa) in tension at the time of application. For other substrates, please contact Sikafloor Technical Services.

MIXING

Mixing Ratio - 2 : 1 by volume.

For bulk packaging, when not mixing full units, each component must be pre-mixed separately to ensure product uniformity.

Primer and Intermediate:

Premix each component separately. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin). Mix the combined components for at least 3 minutes using a low speed drill (300–450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the

Product Data Sheet

Sikafloor®-161

December 2024, Version 05.03

020811020010000049

mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

APPLICATION

Apply primer by squeegee at the rate of 160–266 ft² / US gal (3.4 – 6.5 m² / L) at 6–10 mils (0.15–0.25 mm) wet film thickness (w.f.t.) and back roll. Coverage will vary depending on the porosity of the prepared floor. Product has a limited Pot Life, see Typical Data. Do not apply by dipping roller into mixing container. Pour a bead of product in the form of a ribbon on the surface to be coated, then spread with squeegee and back roll. Ensure that the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire concrete substrate. If necessary, apply an additional coat to ensure the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire concrete substrate.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of

installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
Sikafloor®-161
December 2024, Version 05.03
020811020010000049

Sikafloor-161-en-US-(12-2024)-5-3.pdf



PRODUCT DATA SHEET

Sikafloor®-264

VERSATILE PIGMENTED EPOXY RESIN FOR HIGH PERFORMANCE FLOOR FINISHES

PRODUCT DESCRIPTION

Sikafloor®-264 is a pigmented, two part low viscosity, epoxy coating / binder used for smooth and textured coatings and/or broadcast overlayments.

USES

Sikafloor®-264 may only be used by experienced professionals.

Roller coat and self-leveling slurry for concrete surfaces, with medium to heavy duty wear (e.g. storage, hallways, corridors and assembly halls, maintenance workshops, garages and loading ramps), or as a seal coat for broadcast systems.

CHARACTERISTICS / ADVANTAGES

- Good chemical and abrasion resistance
- Easily applied with brush, roller and squeegee
- Glossy aesthetic finish
- Slip resistant surface possible
- Durable, impermeable and seamless
- Solvent-free, low odor
- Low mixed viscosity

PRODUCT INFORMATION

Packaging	Component A	3.0 US gal. (11.4 L) fill in 5 gallon pail
	Component B	1.5 US gal. (5.7 L) fill in 2 gallon pail
	Components A+B	4.5 US gal. (17 L)
	Component A	(2) 50 US gal. (189 L)
	Component B	50 US gal. (189 L)
	Components A+B	150 US gal. (568 L)
Appearance / Color	Sikafloor standard epoxy colors. (18 standard colors). Refer to Standard Color Selection Guide. Custom colors available. Refer to current price list for availability.	
Shelf Life	24 months in unopened container	
Storage Conditions	Store dry between 40 °F (4 °C) and 90 °F (32 °C).	

TECHNICAL INFORMATION

Shore D Hardness	80 - 85	ASTM D2240 at 73 °F (23 °C) and 50% R.H
Abrasion Resistance	90 mg loss (CS-17/1000 rot/1000 g)	ASTM D4060 at 73 °F (23 °C) and 50% R.H
Impact Strength	0.26 ft/lb (0.35 J)	ASTM 2794 at 73 °F (23 °C) and 50% R.H
Compressive Strength	7,426 psi (51.2 Mpa)	ASTM C579 at 73 °F (23 °C) and 50% R.H
Flexural Strength	8,558 psi (59 MPa)	ASTM D790 at 73 °F (23 °C) and 50% R.H
Tensile Strength	4,902 psi (33.8 MPa)	ASTM D638 at 73 °F (23 °C) and 50% R.H
Elongation at Break	8.3 %	ASTM D638 at 73 °F (23 °C) and 50% R.H
Tensile Adhesion Strength	>400psi (2.7 MPa) (100 % concrete failure)	ASTM D7234 at 73 °F (23 °C) and 50% R.H
Chemical Resistance	Please consult Sikafloor Technical Services	
Permeability to Water Vapor	0.33 g/hour/sq-meter	ASTM E96 at 73 °F (23 °C) and 50% R.H
Coefficient of Friction	0.6	ANSI 326.3 at 73 °F (23 °C) and 50% R.H
Water Absorption	0.05% 2 hours boiling	ASTM C413 at 73 °F (23 °C) and 50% R.H
Gloss level	90 (at 60 degrees)	ASTM D523 at 73 °F (23 °C) and 50% R.H

APPLICATION INFORMATION

Mixing Ratio	2 Parts A to 1 Part B by volume			
Coverage	Smooth Finish Coating:	Prime coat: 160 - 266 ft ² / US gal (3.9 - 5.4 m ² / L) at 6 - 10 mils (0.15 - 0.25 mm) wet film thickness (w.f.t.) Wear coat: 105 - 135 ft ² / US gal (2.6 - 3.3 m ² / L) at 12 - 15 mils (0.30 - 0.38 mm) wet film thickness (w.f.t.)		
	Slurry Layer:	40 ft ² / US gal.* @ 60 mils 30 ft ² / US gal.* @ 80 mils 20 ft ² / US gal.* @ 120 mils		
		For a full ready to mix unit (4.5 Mixed US gal.) of Sikafloor®-264 add 50 Lbs. of Sikadur®-504 filler. The use of a different filler other than Sikadur®-504, may change the theoretical coverage rates as displayed above		
Pot Life	Material Temperature	Time		
	50 °F (10 °C)	~ 50 minutes		
	68 °F (20 °C)	~ 25 minutes		
	86 °F (30 °C)	~ 15 minutes		
Cure Time	Ambient & Substrate Temperature	Foot traffic	Light traffic	Full cure
	50 °F (10 °C)	~ 24 hours	~ 3 days	~ 10 days
	68 °F (20 °C)	~ 12 hours	~ 2 days	~ 7 days
	86 °F (30 °C)	~ 8 hours	~ 36 hours	~ 4 days
Waiting / Recoat Times	Ambient & Substrate Temperature	Minimum	Maximum	
	50 °F (10 °C)	24 hours	48 hours	
	68 °F (20 °C)	8 hours	24 hours	
	86 °F (30 °C)	6 hours	12 hours	

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

Notes on Limitations

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During

installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

Substrate Moisture Content: Moisture content of concrete substrate must be ≤ 4 % by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation to CSP-3 to CSP-4 as per ICRI guidelines). Do not apply to concrete substrate with moisture levels > 4 % mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete

Product Data Sheet

Sikafloor®-264

March 2025, Version 08.04

020811020020000055

BUILDING TRUST



moisture meter. If moisture content of concrete substrate is > 4 % by mass (pbw - part by weight) but < 6% as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor®-1620. If moisture content is ≥ 6%, use Sikafloor® 22 NA or 24 NA PurCem®.

When relative humidity tests for concrete substrate are conducted per ASTM F2170 for project specific requirements, values must be ≤ 85 %. If values are > 85 % but < 96% according to ASTM F2170 use Sikafloor®-1620. If values are ≥ 96%, use Sikafloor® 22 NA or 24 NA PurCem®.

Material Temperature: Precondition material for at least 24 hours between 65 °F to 75°F (18 °C to 24 °C)

Ambient Temperature: Minimum/Maximum 50/85 °F (10/30 °C)

Substrate Temperature: Minimum/Maximum 50/85°F (10/30°C). Substrate temperature must be at least 5 °F (3 °C) above measured Dew Point. Mixing and Application must adhere to Material, Ambient and Substrate temperatures listed above or a decrease in product workability and slower cure rates will occur.

Ambient Relative Humidity: Maximum ambient humidity 85 % (during application and curing)

Dew Point: Beware of condensation!

The substrate must be at least 5 °F (3 °C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur. Ensure there is no vapor drive at the time of application. Refer to ASTM D4263, may be used for a visual indication of vapor drive.
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings
- Do not apply Sikafloor to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- Any aggregate used with Sikafloor systems must be non-reactive and oven-dried.
- This product is not designed for negative side waterproofing.
- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).

- Beware of air flow and changes in air flow. Introduction of dust, debris, and particles, etc. may result in surface imperfections and other defects.
- For professional use only by experienced applicators.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, form oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit a good bond.

Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI - CSP 3 - 4. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

Primer or Smooth Finish Coating

Sikafloor®-264 may be used as a primer on concrete substrates for Sikafloor Coating Systems subjected to light traffic. Please refer to the most current and respective Product Data Sheet for further information.

Priming for concrete substrate is required. If Sikafloor-264 is not used, use another Sikafloor primer. Allow the primer to cure (varies with temperature and humidity) until tack free before applying subsequent coats. Ensure that the primer is pore-free, pinhole-free and provides uniform and complete coverage over the entire substrate. If necessary, apply an additional coat to ensure the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate.

MIXING

Mixing Ratio - 2 : 1 by volume

Product Data Sheet

Sikafloor®-264

March 2025, Version 08.04

020811020020000055

Each component must be pre-mixed separately to ensure product uniformity.

Do not hand mix Sikafloor materials. Mechanically mix only. Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Use of thinners will void any applicable Sika warranty. Improper mixing procedure or incorrect mixing ratio may result in moisture sensitivity, whitening, slow cure, soft spots, and other defects.

Primer and Wear Coat:

Premix each component separately. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin). Mix the combined components for at least 3 minutes using a low speed drill (300 - 450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

Self-leveling Slurry:

Premix each component separately. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin). Mix the combined components for at least 1 minute using a low speed drill (300 - 450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Add Sikadur-504 filler and mix for additional 2 minutes. Be careful not to introduce any air while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the slurry. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing. Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

APPLICATION

Primer

If utilizing Sikafloor®-264 as a primer, apply by squeegee at the rate of 160 - 266 ft² / US gal (3.4 - 5.4 m² / L) at 6 - 10 mils (0.15 - 0.25 mm) wet film thickness (w.f.t.) and back roll within 15 minutes. Coverage will vary depending on the porosity of the prepared floor. Product has a limited pot life, see Typical Data. Do not

apply by dipping roller into mixing container. Pour a bead of product in the form of a ribbon on the surface to be coated, then spread with squeegee and back roll. Ensure that the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire concrete substrate. If necessary, apply an additional coat to ensure the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire concrete substrate.

Wear and Sealer Coat

Sikafloor®-264 is applied with a 15 - 20 mil (0.37 - 0.5 mm) notched squeegee over a smooth surface and a flat squeegee over a rough or broadcast quartz surface. Back rolling is typically done with an 18 inch (455 mm) wide 3/8 inch (10 mm) nap, solvent-resistant roller cover. Back roll the Sikafloor®-264 only to level the squeegee applied material. Over-rolling and late back rolling may cause bubbling and leave roller marks.

Smooth Finish Self-Leveling Slurry

Pour a bead of product on the surface to be coated, then spread with a notched squeegee or pin rake to the desired thickness (60 - 120 mils). Roll immediately (within max. 10 minutes of application) in two directions with a spiked roller to ensure even thickness and the removal of entrapped air. To obtain a higher aesthetic finish, spike roll in two directions at a 90 degree angle by passing only once in each direction. The product has a limited pot life, see Typical Data.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in

any Sika literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the Sika product.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Sika SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. Sika SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of Sika products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sikafloor®-264
March 2025, Version 08.04
020811020020000055

Sikafloor-264-en-US-(03-2025)-8-4.pdf



PRODUCT DATA SHEET

Sikafloor®-340

ABRASION AND UV RESISTANT ALIPHATIC URETHANE

PRODUCT DESCRIPTION

Sikafloor®-340 is an aliphatic urethane with excellent chemical resistance and UV resistance.

USES

Sikafloor®-340 may only be used by experienced professionals.

Sikafloor®-340 is typically used in areas such as aircraft hangars, light to medium traffic areas, where light reflectance and chemical resistance to spills are required. It can be used as two part clear and three part pigmented coating.

CHARACTERISTICS / ADVANTAGES

- VOC compliant in 340 g/L regulated districts
- Excellent UV resistance
- Light reflectance
- Good stain resistance
- High abrasion resistance
- Excellent chemical resistance
- Wide range of colors using Sikafloor Urethane Color Additive
- Clear or Pigmented

PRODUCT INFORMATION

Packaging

*Only recommended for pigmented use

Component A	(2) 1.5 gal (5.29 L) fill in 2 gal pail
Component B	(2) 1 gal (3.78 L) fill in 2 gal pail
Components kit	5 gal(2A +2B)

*Only recommended for clear use

Component A	(2) 2 gal (7.57 L) fill in 2 gal pail
Component B	(2) 1 gal (5.29 L) fill in 2 gal pail
Components kit	6 gal (2A+2B)

Component A	(2) 5 gal (8.93 L) fill in 5 gal pail
Component B	5 gal (8.93 L) fill in 5 gal pail
Components kit	15 gal (2A +B)

Only recommended for clear use

Appearance / Color

Clear or pigmented with Sikafloor® Polyurethane Color Additive; 1-quart (0.95 L) size per 2.5 mixed US gallon.

Shelf Life

24 months in original unopened container under proper storage conditions

Product Data Sheet

Sikafloor®-340

May 2021, Version 01.03

020812040020000012

Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 41 °F (5 °C) and 86 °F (30 °C).		
Volatile organic compound (VOC) content	279 g/l 282 g/l	(A+B) Combined (A+B) Combined + Sikafloor-372 urethane Accelerator Combined	

TECHNICAL INFORMATION

Shore D Hardness	80	ASTM D2240 at 73°F (23°C) and 50% R.H
Abrasion Resistance	27 mg loss (CS-17/1000 rotations/1000g)	ASTM D4060 at 73°F (23°C) and 50% R.H
Tensile Strength	6,745 psi (46 Mpa)	ASTM D638 at 73°F (23°C) and 50% R.H
Elongation at Break	4.0%	ASTM D4541 at 73°F (23°C) and 50% R.H
Tensile Adhesion Strength	435 Psi (3 MPa)	ASTM D4541 at 73°F (23°C) and 50% R.H
Indentation	5.2%	MIL-PRF-24613
Chemical Resistance	Please consult Sikafloor® Technical Services.	
Coefficient of Friction	0.45 Wet /0.68 Dry	ANSI 326.3

APPLICATION INFORMATION

Mixing Ratio	Pigmented: 1.5:1 by volume Clear: 2 : 1 by volume.			
Coverage	Depending upon profile of existing surface, coverage is approximately 350 ft² per gallon (8.6m²/L) per coat, Clear at 350–400 ft² per gallon (8.6–9.8 m2 /L) at 4–5 wet mils Wet: 4.0–5.0 mils / coat Dry: 2.0–3.0 mils / coat Two (2) coats are suggested over a primed surface (The above figures do not allow for surface profile or wastage)			
Pot Life	Material Temperature	Time		
	50 °F (10 °C)	~ 45 minutes		
	68 °F (20 °C)	~ 30 minutes		
	86 °F (30 °C)	~ 15 minutes		
	*Do not apply after indicated Pot Life is exceeded. End of Pot Life is not visible.			
Cure Time	Ambient & Substrate Temperature	Foot traffic	Light traffic	Full cure
	50 °F (10 °C)	~ 24 hours	~ 6 days	~ 10 days
	68 °F (20 °C)	~ 12 hours	~ 4 days	~ 7 days
	86 °F (30 °C)	~ 6 hours	~ 2 days	~ 5 days

50 °F (10 °C)

~ 24 hours

~ 3 days

68 °F (20 °C)

~ 8 hours

~ 2 days

86 °F (30 °C)

~ 6 hours

~ 1 days

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

Notes on Limitations:

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

Substrate Moisture Content: Moisture content of concrete substrate must be $\leq 4\%$ by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation to CSP-3 to CSP-4 as per ICRI guidelines). Do not apply to concrete substrate with moisture levels $> 4\%$ mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter. If moisture content of concrete substrate is $> 4\%$ by mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor® 1610 or Sikafloor® 24 NA PurCem. When relative humidity tests for concrete substrate are conducted per ASTM F2170 for project specific requirements, values must be $\leq 85\%$. If values are $> 85\%$ according to ASTM F2170 use Sikafloor® 1610 or Sikafloor® 24 NA PurCem. ASTM F2170 testing is not a substitute for measuring substrate moisture content with a Tramex® CME/CMExpert type concrete moisture meter as described above.

Material Temperature: Precondition material for at least 24 hours between 65 °F and 75 °F (18–24 °C)

Ambient Temperature: Minimum/Maximum 50/85 °F (10/30 °C)

Substrate Temperature: Minimum/Maximum 50/85 °F (10/30 °C). Substrate temperature must be at least 5 °F (3 °C) above measured Dew Point. Mixing and Application attempted at Material, Ambient and/or Substrate Temperature conditions less than 65 °F (18 °C)

will result in a decrease in product workability and slower cure rates.

Relative Ambient Humidity:

- Minimum ambient humidity 30 %
- Maximum ambient humidity 75 % (during application and curing)

Dew Point: Beware of condensation!

The substrate must be at least 5 °F (3 °C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

Mixing: Do not hand mix Sikafloor materials.

Mechanically mix only.

Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Use of thinners will void any applicable Sika warranty.

Application: Apply the coating to the prepared substrate which should be pore-free and pinhole-free. If necessary, apply an additional coat of a suitable material to ensure the substrate is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate.

- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur. Ensure there is no vapor drive at the time of application. Refer to ASTM D4263, may be used for a visual indication of vapor drive.
- Freshly applied material should be protected from dampness, condensation and water for at least 72 hrs.
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings.
- Do not apply Sikafloor® to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor® product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- Any aggregate used with Sikafloor® systems must be non-reactive and oven-dried.
- This product is not designed for negative side waterproofing.
- Typically not recommended for exterior slabs on grade where freeze/thaw conditions may exist.

- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).
- Beware of air flow and changes in air flow. Introduction of dust, debris, and particles, etc. may result in surface imperfections and other defects.
- Vapors from this product can be objectionable to people unaccustomed to the odor; do not apply in or around buildings occupied by non-construction personnel without consulting building management.
- Do not apply at a mil thickness greater than recommended. Too thick of an application may result in solvent entrapment and improper curing.
- For professional use only by experienced applicators.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, form oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit a good bond.

Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI - CSP 3-6. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

Primer

Priming for concrete substrate is required. Prime with either Sikafloor-161, Sikafloor-1610, Sikafloor- 165 FS or Sikafloor-2570 WB. Allow the primer to cure (varies with temperature and humidity) until tack free before applying subsequent coats. Ensure that the primer is pore-free, pinhole-free and provides uniform and complete coverage over the entire substrate. Please refer to the most current and respective Product Data Sheet for further information.

MIXING

Field Pigmented Mixing Ratio - 1.5:1 by volume + 1 quart Sikafloor Polyurethane Color Additive.

Premix each component separately. If color is desired, the appropriate Sikafloor® Urethane Color Additive is added to Component A at a rate of 1 quart per 2.50 mixed gallons (i.e. Components A+B). Mix Component A (Isocyanate) and Sikafloor Polyurethane Color Additive for 2 minutes or until a uniform color is achieved with a low speed drill (300–450 rpm) and Exomixer or Jiffy type paddle suited to the volume. Empty component - B (Catalyst) in the correct mix ratio to component - A (Isocyanate) and mix for additional 2 minutes. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in coating. During the mixing operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

Clear Resin: Mixing Ratio - 2 : 1 by volume.

Premix each component separately and divide each component into smaller portion (i.e. 2 gal. Component - A and 1 gal. Component - B). Empty contents of Component A or correctly measured part of such into a suitably sized and clean mixing container and add contents of Component B or correct ratio of such. Prepare only that quantity which can be used within the pot life of the material. Mix the combined components for at least 3 minutes using a low speed drill (300–450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

For bulk packaging, when not mixing full units, each component must be pre-mixed separately to ensure product uniformity.

Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

APPLICATION

Pour a thin bead (approximately 6"-12" wide) of Sikafloor®-340 on the surface, use a flat squeegee to distribute the material evenly and back roll. Back roll the Sikafloor®-340 only to level the thickness of material applied. Do not apply in excess of 5 mils (0.125mm) WFT, failure of the coating may occur. Divide the floor into sections (at expansion joints or doorways when possible) that can be completed without stopping. Where a section will end, it should be taped off to form a straight line providing a clean edge for an adjacent section. Back rolling is typically done with an 18-inch (.5 m) short nap, 3/8-inch (9.5 mm), solvent resistant roller cover. Overrolling may cause non-uniform sections and bubbling.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet


Sikafloor®-340
May 2021, Version 01.03
020812040020000012

Sikafloor-340-en-US-(05-2021)-1-3.pdf



SIKAFLOOR® STANDARD COLOR GUIDE

SIKAFLOOR MULTIDUR SYSTEMS, SIKAFLOOR SEP-N &
SCO COLOR ADDITIVES, SIKAGARD WB WALL SYSTEMS




SILVER GRAY*



LIGHT GRAY



OXFORD GRAY*



WINDOW GRAY



TRAFFIC GRAY*



BEIGE ROSE*



GRAY BEIGE*



SIGNAL YELLOW*



JET BLACK*



RAFFIA BEIGE



BEIGE



TAN 251



BASALT GRAY



TRAFFIC BLUE



PALE GREEN



OXIDE RED



TRAFFIC RED*



SIGNAL WHITE*

Note:

Sikafloor 2540 W NA and Sikagard WB Wall Systems are available in the above color names that are followed by *.

BUILDING TRUST



STANDARD COLORS:

The above colors will ship within 2 to 3 (two to three) business days from receipt of order. Day one begins the day after the order is received. Orders must be submitted by 4 PM EST.

CUSTOM COLORS:


A custom color is defined as any color that is not in this color chart. For example a color match requested from a color chip, or a paint sample, etc.

Custom color matching will take 5 business days from receipt of Color Standard.

(Please call your customer service representative for details on where to mail your standard.

Once color standard is matched, a drawdown card will be mailed to the customer for approval. After color approval and receipt of Purchase Order, custom colors will ship within 3 to 5 business days. Day one begins the next business day after the order is received.

Because of the limitations of process color printing, the color samples contained herein are close approximations of actual colors and should not be relied upon for true color. Colors show approximate tone without any texture. Final color matching should be made with an actual sample of the product, color and texture to be used. Gloss level will vary depending on product used. Custom colors are available. Minimum quantities, adequate lead time and up-charges may apply. For use with compatible Sikafloor® products only. Please consult Sika Industrial Flooring for further information and pricing.

**SIKA USA FLOORING**

201 Polito Avenue
Lyndhurst NJ 07071
Tel: 844 529 7101
Fax: 800 294 6408
www.SikaFloorUSA.com

BUILDING TRUST

PRODUCT DATA SHEET

Sikafloor®-293

CLEAR EPOXY COVE RESIN

PRODUCT DESCRIPTION

Sikafloor®-293 is a thixotropic binder resin specifically designed for cove and vertical applications. Sikafloor®-293, when mixed with Sikafloor- Decorative® Quartz, Sikadur®-505, - 506, -506ER,- 506RC and - 508 aggregates, may be applied up to 1/4" thick vertically.

USES

Sikafloor®-293 may only be used by experienced professionals.

Sikafloor®-293 is used where the maximum Sanitation/Hygiene is required. It can provide rounded and sealed corners.

CHARACTERISTICS / ADVANTAGES

- Designed specifically for trowel application on vertical surfaces
- Good mechanical resistance
- Versatile usage with other Sikafloor systems
- Excellent adhesion

PRODUCT INFORMATION

Packaging	Component A	1.5 US gallon (5.6 L) fill in 2 gallon pail
	Component B	0.5 US gallon (1.8 L) fill in 1 gallon can
	Components A+B:	2.0 US gallon kit (7.57 L)
Appearance / Color	Neutral/Clear or pigmented with Sikafloor Epoxy Pigment Packs	
Shelf Life	2 years in original unopened container under proper storage	
Storage Conditions	Store dry between 40 - 90 °F (4 - 32 °C)	

TECHNICAL INFORMATION

Shore D Hardness	80 - 85	ASTM D2240 at 73 °F (23 °C) and 50% R.H
Impact Strength	2.62 ft.lb	ASTM D2794 at 73 °F (23 °C) and 50% R.H
Compressive Strength	7,832 psi (54 MPa)	ASTM C579 at 73 °F (23 °C) and 50% R.H
Flexural Strength	2,132 psi (14.7 MPa)	ASTM C580 at 73 °F (23 °C) and 50% R.H
Tensile Strength	2,031 psi (14 MPa)	ASTM C307 at 73 °F (23 °C) and 50% R.H
Tensile Adhesion Strength	725 psi (>5 MPa)	ASTM D7234 at 73 °F (23 °C) and 50% R.H
Thermal Resistance	Pass	ASTM C844 at 73 °F (23 °C) and 50% R.H
Indentation	0.40%	ASTM Mil-PRF-24613 at 73 °F (23 °C) and 50% R.H
Water Absorption	1.2% (24 hours boiling)	ASTM C413 at 73 °F (23 °C) and 50% R.H

APPLICATION INFORMATION

Mixing Ratio	3 : 1 by volume plus approximately 45 - 60 pounds of the aforementioned Sikafloor-Decorative® Quartz and Sikadur® aggregates per gallon of mixed Sikafloor®-293	
Coverage	As a primer, applied at 4 - 6 wet mils vertically. For cove application, applied at approximately 50 In.ft. per gallon with specified aggregates at 1/8" thick at 4" high. Coverage rates are calculated based on material needed for finishing of smooth surfaces.	
Substrate Temperature	50 °F (10 °C) min. / 95 °F (35 °C) max.	
Pot Life	Material Temperature	Time
	50 °F (10 °C)	~ 40 minutes

Cure Time	Ambient & Substrate Temperature	Light Traffic	Full Cure
	50 °F (10 °C)	~ 3 days	~ 10 days
	68 °F (20 °C)	~ 2 days	~ 7 days
	86 °F (30 °C)	~ 1 day	~ 4 days

Waiting / Recoat Times	Ambient & Substrate Temperature	Time Minimum
	50 °F (10 °C)	~ 20 hours
	68 °F (20 °C)	~ 6 hours
	86 °F (30 °C)	~ 3 hours

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

Notes on Limitations:

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

Substrate Moisture Content: Moisture content of concrete substrate must be $\leq 4\%$ by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation to CSP-3 to CSP-4 as per ICRI guidelines). Do not apply to concrete substrate with moisture levels $> 4\%$ mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter. If moisture content of concrete substrate is $> 4\%$ by mass (pbw – part by weight) but $< 6\%$ as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor®-1620. If moisture content is $\geq 6\%$, use Sikafloor® 22 NA or 24 NA PurCem®.

When relative humidity tests for concrete substrate are conducted per ASTM F2170 for project specific requirements, values must be $\leq 85\%$. If values are $> 85\%$ but $< 96\%$ according to ASTM F2170 use Sikafloor®-1620. If values are $\geq 96\%$, use Sikafloor® 22 NA or 24 NA PurCem®.

Material Temperature: Precondition material for at least 24 hours between 65 °F to 75 °F (18 °C to 24 °C)

Ambient Temperature: Minimum/Maximum 50/85 °F (10/30 °C)

Substrate Temperature: Minimum/Maximum 50/85 °F (10/30 °C). Substrate temperature must be at least 5 °F (3 °C) above measured Dew Point. Mixing and Application must adhere to Material, Ambient and Substrate temperatures listed above or a decrease in product workability and slower cure rates will occur.

Ambient Relative Humidity: Maximum ambient humidity 85% (during application and curing)

Dew Point: Beware of condensation! The substrate must be at least 5 °F (3 °C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

Mixing: Do not hand mix Sikafloor materials. Mechanically mix only. Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Use of thinners will void any applicable Sika warranty. Improper mixing procedure or incorrect mixing ratio may result in moisture sensitivity, whitening, slow cure, soft spots, and other defects.

Application: Apply the primer to the prepared substrate using a squeegee and back roll to provide uniform coverage. Ensure that the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate. If necessary, apply an additional coat to ensure the coating is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate.

- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur. Ensure there is no vapor drive at the time of application. Refer to ASTM D4263, may be used for a visual indication of vapor drive.
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings
- Do not apply Sikafloor to concrete substrate containing aggregates susceptible to ASR (Alkali Silica

Product Data Sheet

Sikafloor®-293

March 2025, Version 03.01

020811020010000096

BUILDING TRUST



Reaction) due to risk of natural alkali redistribution below the Sikafloor product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.

- Any aggregate used with Sikafloor systems must be non-reactive and oven-dried.
- This product is not designed for negative side waterproofing.
- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).
- Beware of air flow and changes in air flow. Introduction of dust, debris, and particles, etc. may result in surface imperfections and other defects.
- For professional use only by experienced applicators.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

SURFACE PREPARATION

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, form oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit a good bond. Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI - CSP 3-6.

The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application. Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for a recommendation.

Primer

Apply Sikafloor®-293 or another Sikafloor epoxy primer at approximately 4 - 6 mils. If the primer will be cured prior to the application of the cove, it is recommended to broadcast an angular aggregate to assist in creating a tooth or roughened surface for the wet cove material to grab.

MIXING

Mixing Ratio: 3: 1 by volume plus approximately 45-60 pounds of the aforementioned Sikafloor-Decorative® Quartz and Sikadur® aggregates per gallon

of mixed Sikafloor®-293.

Mix the combined components for at least 1 minute using a low speed drill (300–450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

Transfer the mixed binder (components A+B) into a suitable mechanical mixer. Gradually add specified aggregates (component C) to the binder. Once all ingredients are combined, mix continuously and thoroughly for 2 to 4 minutes to ensure complete mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the mortar. Immediately transfer the materials onto the floor where the cove is to be installed.

Do not mix more material that can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

APPLICATION

The use of a low level light along the floor/wall intersection will show shadows and aide in reducing trowel marks or ridges. After thoroughly mixing, immediately deliver material along the floor/wall. Apply the material by striking it up the wall with a steel trowel or margin trowel, ensure the thickness is consistent. Keep the trowel clean by wiping with a rag dampened with solvent. The solvent will act as a lubricant to assist in troweling, do not use water. Finish with a cove trowel.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the

obligation to read and follow the warnings and instructions for each Sika product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the Sika product.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Sika SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. Sika SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of Sika products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sikafloor®-293
March 2025, Version 03.01
020811020010000096

Sikafloor-293-en-US-(03-2025)-3-1.pdf





Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

SECTION 1. IDENTIFICATION

Product name : Sikafloor®-161 Part A

Company name : Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
USA
www.sikausa.com

Telephone : (201) 933-8800

Telefax : (201) 804-1076

E-mail address : ehs@sika-corp.com

Emergency telephone : CHEMTREC: 800-424-9300
INTERNATIONAL: +1-703-527-3887

Recommended use of the chemical and restrictions on use : For further information, refer to product data sheet.

SECTION 2. HAZARDS IDENTIFICATION

GHS classification in accordance with the OSHA Hazard Communication Standard (29 CFR 1910.1200)

Skin irritation : Category 2

Eye irritation : Category 2A

Skin sensitization : Category 1

Carcinogenicity (Inhalation) : Category 1A

Reproductive toxicity : Category 1B

Specific target organ toxicity : Category 3 (Respiratory system)
- single exposure

Specific target organ toxicity : Category 1 (Lungs)
- repeated exposure

GHS label elements



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

Hazard pictograms

:



Signal Word

:

Danger

Hazard Statements

:

H315 Causes skin irritation.
H317 May cause an allergic skin reaction.
H319 Causes serious eye irritation.
H335 May cause respiratory irritation.
H350 May cause cancer by inhalation.
H360 May damage fertility or the unborn child.
H372 Causes damage to organs (Lungs) through prolonged or repeated exposure.

Precautionary Statements

:

Prevention:

P201 Obtain special instructions before use.
P202 Do not handle until all safety precautions have been read and understood.
P260 Do not breathe mist or vapors.
P264 Wash skin thoroughly after handling.
P270 Do not eat, drink or smoke when using this product.
P271 Use only outdoors or in a well-ventilated area.
P272 Contaminated work clothing must not be allowed out of the workplace.
P280 Wear protective gloves/ protective clothing/ eye protection/ face protection.

Response:

P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
P304 + P340 + P312 IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a POISON CENTER/ doctor if you feel unwell.
P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P308 + P313 IF exposed or concerned: Get medical advice/ attention.
P333 + P313 If skin irritation or rash occurs: Get medical advice/ attention.
P337 + P313 If eye irritation persists: Get medical advice/ attention.
P362 + P364 Take off contaminated clothing and wash it before reuse.

Storage:

P403 + P233 Store in a well-ventilated place. Keep container tightly closed.
P405 Store locked up.



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

Disposal:

P501 Dispose of contents/ container to an approved waste disposal plant.

Additional Labeling

There are no ingredients with unknown acute toxicity used in a mixture at a concentration $\geq 1\%$.

Other hazards

None known.

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS

Mixtures

Components

Chemical name	CAS-No.	Classification	Concentration (% w/w)
Quartz (SiO ₂) >5µm	14808-60-7	Carc. 1A; H350 STOT RE 1; H372 STOT SE 3; H335	$\geq 30 - < 50$
bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)	25068-38-6	Skin Irrit. 2; H315 Eye Irrit. 2A; H319 Skin Sens. 1; H317	$\geq 30 - < 50$
bisphenol-F-(epichlorhydrin) epoxy resin	28064-14-4	Skin Irrit. 2; H315 Eye Irrit. 2A; H319 Skin Sens. 1; H317	$\geq 10 - < 20$
oxirane, mono[(C12-14-alkyloxy)methyl]derivatives	68609-97-2	Skin Irrit. 2; H315 Skin Sens. 1; H317 Repr. 1B; H360	$\geq 1 - < 5$

Actual concentration is withheld as a trade secret

SECTION 4. FIRST AID MEASURES

- General advice : Move out of dangerous area.
Consult a physician.
Show this material safety data sheet to the doctor in attendance.
- If inhaled : Move to fresh air.
Consult a physician after significant exposure.
- In case of skin contact : Take off contaminated clothing and shoes immediately.
Wash off with soap and plenty of water.
If symptoms persist, call a physician.
- In case of eye contact : Immediately flush eye(s) with plenty of water.
Remove contact lenses.
Keep eye wide open while rinsing.



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

	If eye irritation persists, consult a specialist.
If swallowed	: Clean mouth with water and drink afterwards plenty of water. Do not induce vomiting without medical advice. Do not give milk or alcoholic beverages. Never give anything by mouth to an unconscious person. Obtain medical attention.
Most important symptoms and effects, both acute and delayed	: Cough Respiratory disorder Allergic reactions Excessive lachrymation Erythema Dermatitis Causes skin irritation. May cause an allergic skin reaction. Causes serious eye irritation. May cause respiratory irritation. May cause cancer by inhalation. May damage fertility or the unborn child. Causes damage to organs through prolonged or repeated exposure. irritant effects sensitizing effects toxic effects for reproduction
Notes to physician	: Treat symptomatically.

SECTION 5. FIRE-FIGHTING MEASURES

Suitable extinguishing media	: Use extinguishing measures that are appropriate to local circumstances and the surrounding environment.
Further information	: Collect contaminated fire extinguishing water separately. This must not be discharged into drains. Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.
Special protective equipment for fire-fighters	: In the event of fire, wear self-contained breathing apparatus.

SECTION 6. ACCIDENTAL RELEASE MEASURES

Personal precautions, protective equipment and emergency procedures	: Use personal protective equipment. Deny access to unprotected persons.
Environmental precautions	: Do not flush into surface water or sanitary sewer system. If the product contaminates rivers and lakes or drains inform



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

respective authorities.
Local authorities should be advised if significant spillages cannot be contained.

Methods and materials for containment and cleaning up : Soak up with inert absorbent material (e.g. sand, silica gel, acid binder, universal binder, sawdust).
Keep in suitable, closed containers for disposal.

SECTION 7. HANDLING AND STORAGE

Advice on protection against fire and explosion : Normal measures for preventive fire protection.

Advice on safe handling : Avoid exceeding the given occupational exposure limits (see section 8).
Do not get in eyes, on skin, or on clothing.
For personal protection see section 8.
Persons with a history of skin sensitization problems or asthma, allergies, chronic or recurrent respiratory disease should not be employed in any process in which this mixture is being used.
Smoking, eating and drinking should be prohibited in the application area.
Pregnant women or women of child-bearing age should not be exposed to this product.
Follow standard hygiene measures when handling chemical products.

Conditions for safe storage : Store in original container.
Keep in a well-ventilated place.
Containers which are opened must be carefully resealed and kept upright to prevent leakage.
Observe label precautions.
Store in accordance with local regulations.

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Ingredients with workplace control parameters

Components	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
Quartz (SiO ₂) >5µm	14808-60-7	TWA (Respirable particulate matter)	0.025 mg/m ³	ACGIH
		TWA (Respirable dust)	0.05 mg/m ³	OSHA Z-1
		TWA (respir-	10 mg/m ³ /	OSHA Z-3



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

		able)	%SiO ₂ +2	
		TWA (respirable)	250 mppcf / %SiO ₂ +5	OSHA Z-3
		TWA (respirable dust fraction)	0.1 mg/m ³	OSHA P0
		TWA (Respirable particulate matter)	0.025 mg/m ³ (Silica)	ACGIH
		PEL (respirable)	0.05 mg/m ³	OSHA CARC
		TWA (respirable dust fraction)	0.1 mg/m ³	OSHA P0
		TWA (Respirable particulate matter)	0.025 mg/m ³	ACGIH
		TWA (Respirable particulate matter)	0.025 mg/m ³ (Silica)	ACGIH

The above constituents are the only constituents of the product which have a PEL, TLV or other recommended exposure limit. At this time, the other constituents have no known exposure limits.

Engineering measures : Use of adequate ventilation should be sufficient to control worker exposure to airborne contaminants. If the use of this product generates dust, fumes, gas, vapor or mist, use process enclosures, local exhaust ventilation or other engineering controls to keep worker exposure below any recommended or statutory limits.

Personal protective equipment

Respiratory protection : Use a properly fitted NIOSH approved air-purifying or air-fed respirator complying with an approved standard if a risk assessment indicates this is necessary.

The filter class for the respirator must be suitable for the maximum expected contaminant concentration (gas/vapor/aerosol/particulates) that may arise when handling the product. If this concentration is exceeded, self-contained breathing apparatus must be used.

Hand protection : Chemical-resistant, impervious gloves complying with an approved standard should be worn at all times when handling chemical products if a risk assessment indicates this is necessary.



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

Eye protection	:	Safety eyewear complying with an approved standard should be used when a risk assessment indicates this is necessary.
Skin and body protection	:	Choose body protection in relation to its type, to the concentration and amount of dangerous substances, and to the specific work-place.
Hygiene measures	:	Avoid contact with skin, eyes and clothing. Wash hands before breaks and immediately after handling the product. Remove contaminated clothing and protective equipment before entering eating areas. Wash thoroughly after handling.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance	:	liquid
Color	:	light brown
Odor	:	ether-like
Odor Threshold	:	No data available
pH	:	Not applicable
Melting point/ range / Freezing point	:	No data available
Boiling point/boiling range	:	No data available
Flash point	:	266 °F / 130 °C (Method: closed cup)
Evaporation rate	:	No data available
Flammability (solid, gas)	:	No data available
Upper explosion limit / Upper flammability limit	:	No data available
Lower explosion limit / Lower flammability limit	:	No data available
Vapor pressure	:	0.01 hpa
Relative vapor density	:	No data available
Density	:	ca. 1.50 g/cm ³ (73 °F / 23 °C)
Solubility(ies)	:	



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

Water solubility	:	soluble
Solubility in other solvents	:	No data available
Partition coefficient: n-octanol/water	:	No data available
Autoignition temperature	:	No data available
Decomposition temperature	:	No data available
Viscosity		
Viscosity, dynamic	:	No data available
Viscosity, kinematic	:	ca. > 20.5 mm ² /s (104 °F / 40 °C)
Explosive properties	:	No data available
Oxidizing properties	:	No data available
Volatile organic compounds (VOC) content	:	62 g/l Sikafloor®-161 Part A + Sikafloor®-161/264 Part B Combined.

SECTION 10. STABILITY AND REACTIVITY

Reactivity	:	No dangerous reaction known under conditions of normal use.
Chemical stability	:	The product is chemically stable.
Possibility of hazardous reactions	:	Stable under recommended storage conditions.
Conditions to avoid	:	No data available
Incompatible materials	:	No data available
Hazardous decomposition products	:	No decomposition if stored and applied as directed.

SECTION 11. TOXICOLOGICAL INFORMATION

Acute toxicity

Not classified due to lack of data.

Components:

bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700):

Acute oral toxicity	:	LD50 Oral (Rat): > 5,000 mg/kg
Acute dermal toxicity	:	LD50 Dermal (Rabbit): > 20,000 mg/kg



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

bisphenol-F-(epichlorhydrin) epoxy resin:

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

Skin corrosion/irritation

Causes skin irritation.

Serious eye damage/eye irritation

Causes serious eye irritation.

Respiratory or skin sensitization

Skin sensitization

May cause an allergic skin reaction.

Respiratory sensitization

Not classified due to lack of data.

Germ cell mutagenicity

Not classified due to lack of data.

Carcinogenicity

May cause cancer by inhalation.

IARC	Group 1: Carcinogenic to humans	
	Quartz (SiO ₂)	14808-60-7
	(Silica dust, crystalline)	
OSHA	OSHA specifically regulated carcinogen	
	Quartz (SiO ₂)	14808-60-7
	(crystalline silica)	
NTP	Known to be human carcinogen	
	Quartz (SiO ₂)	14808-60-7
	(Silica, Crystalline (Respirable Size))	

Reproductive toxicity

May damage fertility or the unborn child.

STOT-single exposure

May cause respiratory irritation.

STOT-repeated exposure

Causes damage to organs (Lungs) through prolonged or repeated exposure.

Once sensitized, a severe allergic reaction may occur when subsequently exposed to very low levels.

Aspiration toxicity

Not classified due to lack of data.



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

Further information

Product:

Quartz (14808-60-7): This classification is relevant when exposed to Quartz (silicon dioxide) in dust or powder form only, including cured product that is subject to sanding, grinding, cutting, or other surface preparation activities.

SECTION 12. ECOLOGICAL INFORMATION

Ecotoxicity

Components:

bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700):

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 2 mg/l
Exposure time: 96 h

Toxicity to daphnia and other : EC50 (Daphnia magna (Water flea)): 1.8 mg/l
aquatic invertebrates Exposure time: 48 h

Persistence and degradability

No data available

Bioaccumulative potential

No data available

Mobility in soil

No data available

Other adverse effects

Product:

Additional ecological information : Do not empty into drains; dispose of this material and its container in a safe way.
Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.
Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.
May be harmful to the environment if released in large quantities.
Water polluting material.

SECTION 13. DISPOSAL CONSIDERATIONS

Disposal methods

Waste from residues : Disposal of this product, solutions and any by-products should at all times comply with the requirements of environmental



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

protection and waste disposal legislation and any regional local authority requirements.

Contaminated packaging : Empty containers should be taken to an approved waste handling site for recycling or disposal.

SECTION 14. TRANSPORT INFORMATION

International Regulations

IATA-DGR

UN/ID No. : UN 3082
Proper shipping name : Environmentally hazardous substance, liquid, n.o.s.
(epoxy resin)
Class : 9
Packing group : III
Labels : Miscellaneous
Packing instruction (cargo aircraft) : 964
Packing instruction (passenger aircraft) : 964

IMDG-Code

UN number : UN 3082
Proper shipping name : ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID,
N.O.S.
(epoxy resin)
Class : 9
Packing group : III
Labels : 9
EmS Code : F-A, S-F
Marine pollutant : yes

Domestic regulation

49 CFR

Not regulated as a dangerous good

Special precautions for user

The transport classification(s) provided herein are for informational purposes only, and solely based upon the properties of the unpackaged material as it is described within this Safety Data Sheet. Transportation classifications may vary by mode of transportation, package sizes, and variations in regional or country regulations.

SECTION 15. REGULATORY INFORMATION

TSCA list : All chemical substances in this product are either listed as active on the TSCA Inventory or are in compliance with a TSCA Inventory exemption.

No substances are subject to a Significant New Use Rule.



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

No substances are subject to TSCA 12(b) export notification requirements.

CERCLA Reportable Quantity

Listed substances in the product are at low enough levels to not be expected to exceed the RQ

SARA 304 Extremely Hazardous Substances Reportable Quantity

Listed substances in the product are at low enough levels to not be expected to exceed the RQ

SARA 302 Extremely Hazardous Substances Threshold Planning Quantity

This material does not contain any components with a section 302 EHS TPQ.

SARA 311/312 Hazards : Respiratory or skin sensitization
Carcinogenicity
Reproductive toxicity
Specific target organ toxicity (single or repeated exposure)
Skin corrosion or irritation
Serious eye damage or eye irritation

SARA 313 : This material does not contain any chemical components with known CAS numbers that exceed the threshold (De Minimis) reporting levels established by SARA Title III, Section 313.

Clean Air Act

This product does not contain any hazardous air pollutants (HAP), as defined by the U.S. Clean Air Act Section 112 (40 CFR 61).

California Prop. 65

 **WARNING:** This product can expose you to chemicals including Quartz (SiO₂) >5µm, which is known to the State of California to cause cancer, and toluene, which is known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

SECTION 16. OTHER INFORMATION

Full text of other abbreviations

ACGIH	:	USA. ACGIH Threshold Limit Values (TLV)
OSHA CARC	:	OSHA Specifically Regulated Chemicals/Carcinogens
OSHA P0	:	USA. Table Z-1-A Limits for Air Contaminants (1989 vacated values)
OSHA Z-1	:	USA. Occupational Exposure Limits (OSHA) - Table Z-1 Limits for Air Contaminants
OSHA Z-3	:	USA. Occupational Exposure Limits (OSHA) - Table Z-3 Mineral Dusts
ACGIH / TWA	:	8-hour, time-weighted average
OSHA CARC / PEL	:	Permissible exposure limit (PEL)



Sikafloor®-161 Part A

Revision Date 01/16/2025

Print Date 01/16/2025

OSHA P0 / TWA	:	8-hour time weighted average
OSHA Z-1 / TWA	:	8-hour time weighted average
OSHA Z-3 / TWA	:	8-hour time weighted average

Notes to Reader

The information contained in this Safety Data Sheet applies only to the actual Sika Corporation ("Sika") product identified and described herein. This information is not intended to address, nor does it address the use or application of the identified Sika product in combination with any other material, product or process. All of the information set forth herein is based on technical data regarding the identified product that Sika believes to be reliable as of the date hereof. Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's current Product Data Sheet, product label and Safety Data Sheet for each Sika product, which are available at web site and/or telephone number listed in Section 1 of this SDS.

SIKA MAKES NO WARRANTIES EXPRESS OR IMPLIED AND ASSUMES NO LIABILITY ARISING FROM THIS INFORMATION OR ITS USE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES AND SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

All sales of Sika products are subject to its current terms and conditions of sale available at www.sikausa.com or 201-933-8800.

Revision Date 01/16/2025

100000001027
US / Z8



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

SECTION 1. IDENTIFICATION

Product name : Sikafloor®-264 Part A

Company name : Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
USA
www.sikausa.com

Telephone : (201) 933-8800

Telefax : (201) 804-1076

E-mail address : ehs@sika-corp.com

Emergency telephone : CHEMTREC: 800-424-9300
INTERNATIONAL: +1-703-527-3887

Recommended use of the chemical and restrictions on use : For further information, refer to product data sheet.

SECTION 2. HAZARDS IDENTIFICATION

GHS classification in accordance with the OSHA Hazard Communication Standard (29 CFR 1910.1200)

Skin irritation : Category 2

Eye irritation : Category 2A

Skin sensitization : Category 1

Carcinogenicity (Inhalation) : Category 1A

Reproductive toxicity : Category 1B

Specific target organ toxicity : Category 3 (Respiratory system)
- single exposure

Specific target organ toxicity : Category 1 (Lungs)
- repeated exposure

Other hazards

GHS label elements



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

Hazard pictograms

:



Signal Word

: Danger

Hazard Statements

: H315 Causes skin irritation.
H317 May cause an allergic skin reaction.
H319 Causes serious eye irritation.
H335 May cause respiratory irritation.
H350 May cause cancer by inhalation.
H360 May damage fertility or the unborn child.
H372 Causes damage to organs (Lungs) through prolonged or repeated exposure.

Precautionary Statements

: **Prevention:**
P201 Obtain special instructions before use.
P202 Do not handle until all safety precautions have been read and understood.
P260 Do not breathe mist or vapors.
P264 Wash skin thoroughly after handling.
P270 Do not eat, drink or smoke when using this product.
P271 Use only outdoors or in a well-ventilated area.
P272 Contaminated work clothing must not be allowed out of the workplace.
P280 Wear protective gloves/ protective clothing/ eye protection/ face protection.

Response:
P302 + P352 IF ON SKIN: Wash with plenty of soap and water.
P304 + P340 + P312 IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a POISON CENTER/ doctor if you feel unwell.
P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P308 + P313 IF exposed or concerned: Get medical advice/ attention.
P333 + P313 If skin irritation or rash occurs: Get medical advice/ attention.
P337 + P313 If eye irritation persists: Get medical advice/ attention.
P362 + P364 Take off contaminated clothing and wash it before reuse.

Storage:
P403 + P233 Store in a well-ventilated place. Keep container tightly closed.
P405 Store locked up.



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

Disposal:

P501 Dispose of contents/ container to an approved waste disposal plant.

Additional Labeling

There are no ingredients with unknown acute toxicity used in a mixture at a concentration $\geq 1\%$.
None known.

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS

Mixtures

Components

Chemical name	CAS No./Unique ID	Classification	Concentration (% w/w)
Quartz (SiO ₂) >5µm	14808-60-7	Carc. 1A; H350 STOT RE 1; H372 STOT SE 3; H335	$\geq 30 - < 50$
bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)	25068-38-6	Skin Irrit. 2; H315 Eye Irrit. 2A; H319 Skin Sens. 1; H317	$\geq 30 - < 50$
bisphenol-F-(epichlorhydrin) epoxy resin	28064-14-4	Skin Irrit. 2; H315 Eye Irrit. 2A; H319 Skin Sens. 1; H317	$\geq 5 - < 10$
oxirane, mono[(C12-14-alkyloxy)methyl]derivatives	68609-97-2	Skin Irrit. 2; H315 Skin Sens. 1; H317 Repr. 1B; H360	$\geq 1 - < 5$
bisphenol-F-(epichlorhydrin) epoxy resin	9003-36-5	Skin Irrit. 2; H315 Skin Sens. 1; H317	$\geq 1 - < 5$
P-tert-butylphenyl-1-(2,3-epoxy)propyl ether	3101-60-8	Skin Sens. 1; H317	$\geq 1 - < 5$

Actual concentration is withheld as a trade secret

Actual concentration is withheld as a trade secret

SECTION 4. FIRST AID MEASURES

- General advice : Move out of dangerous area.
Consult a physician.
Show this material safety data sheet to the doctor in attendance.
- If inhaled : Move to fresh air.
Consult a physician after significant exposure.
- In case of skin contact : Take off contaminated clothing and shoes immediately.
Wash off with soap and plenty of water.
If symptoms persist, call a physician.



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

In case of eye contact	: Immediately flush eye(s) with plenty of water. Remove contact lenses. Keep eye wide open while rinsing. If eye irritation persists, consult a specialist.
If swallowed	: Clean mouth with water and drink afterwards plenty of water. Do not induce vomiting without medical advice. Do not give milk or alcoholic beverages. Never give anything by mouth to an unconscious person. Obtain medical attention.
Most important symptoms and effects, both acute and delayed	: Cough Respiratory disorder Allergic reactions Excessive lachrymation Erythema Dermatitis Causes skin irritation. May cause an allergic skin reaction. Causes serious eye irritation. May cause respiratory irritation. May cause cancer by inhalation. May damage fertility or the unborn child. Causes damage to organs through prolonged or repeated exposure. irritant effects sensitizing effects toxic effects for reproduction
Notes to physician	: Treat symptomatically.

SECTION 5. FIRE-FIGHTING MEASURES

Suitable extinguishing media	: Use extinguishing measures that are appropriate to local circumstances and the surrounding environment.
Further information	: Collect contaminated fire extinguishing water separately. This must not be discharged into drains. Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.
Special protective equipment for fire-fighters	: In the event of fire, wear self-contained breathing apparatus.

SECTION 6. ACCIDENTAL RELEASE MEASURES

Personal precautions, protective equipment and emergency measures	: Use personal protective equipment. Deny access to unprotected persons.
---	---



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

gency procedures

Environmental precautions : Do not flush into surface water or sanitary sewer system.
If the product contaminates rivers and lakes or drains inform respective authorities.
Local authorities should be advised if significant spillages cannot be contained.

Methods and materials for containment and cleaning up : Soak up with inert absorbent material (e.g. sand, silica gel, acid binder, universal binder, sawdust).
Keep in suitable, closed containers for disposal.

SECTION 7. HANDLING AND STORAGE

Advice on protection against fire and explosion : Normal measures for preventive fire protection.

Advice on safe handling : Avoid exceeding the given occupational exposure limits (see section 8).
Do not get in eyes, on skin, or on clothing.
For personal protection see section 8.
Persons with a history of skin sensitization problems or asthma, allergies, chronic or recurrent respiratory disease should not be employed in any process in which this mixture is being used.
Smoking, eating and drinking should be prohibited in the application area.
Pregnant women or women of child-bearing age should not be exposed to this product.
Follow standard hygiene measures when handling chemical products.

Conditions for safe storage : Store in original container.
Keep in a well-ventilated place.
Containers which are opened must be carefully resealed and kept upright to prevent leakage.
Observe label precautions.
Store in accordance with local regulations.

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Ingredients with workplace control parameters

Components	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
Quartz (SiO ₂) >5µm	14808-60-7	TWA (Respirable particulate mat-	0.025 mg/m ³	ACGIH



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

		ter)		
		TWA (Respirable dust)	0.05 mg/m3	OSHA Z-1
		TWA (respirable)	10 mg/m3 / %SiO ₂ +2	OSHA Z-3
		TWA (respirable)	250 mppcf / %SiO ₂ +5	OSHA Z-3
		TWA (respirable dust fraction)	0.1 mg/m3	OSHA P0
		TWA (Respirable particulate matter)	0.025 mg/m3 (Silica)	ACGIH
		PEL (respirable)	0.05 mg/m3	OSHA CARC
		TWA (respirable dust fraction)	0.1 mg/m3	OSHA P0
		TWA (Respirable particulate matter)	0.025 mg/m3	ACGIH
		TWA (Respirable particulate matter)	0.025 mg/m3 (Silica)	ACGIH

The above constituents are the only constituents of the product which have a PEL, TLV or other recommended exposure limit. At this time, the other constituents have no known exposure limits.

Engineering measures : Use of adequate ventilation should be sufficient to control worker exposure to airborne contaminants. If the use of this product generates dust, fumes, gas, vapor or mist, use process enclosures, local exhaust ventilation or other engineering controls to keep worker exposure below any recommended or statutory limits.

Personal protective equipment

Respiratory protection : Use a properly fitted NIOSH approved air-purifying or air-fed respirator complying with an approved standard if a risk assessment indicates this is necessary.

The filter class for the respirator must be suitable for the maximum expected contaminant concentration (gas/vapor/aerosol/particulates) that may arise when handling the product. If this concentration is exceeded, self-contained breathing apparatus must be used.

Hand protection : Chemical-resistant, impervious gloves complying with an



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

	approved standard should be worn at all times when handling chemical products if a risk assessment indicates this is necessary.
Eye protection	: Safety eyewear complying with an approved standard should be used when a risk assessment indicates this is necessary.
Skin and body protection	: Choose body protection in relation to its type, to the concentration and amount of dangerous substances, and to the specific work-place.
Hygiene measures	: Avoid contact with skin, eyes and clothing. Wash hands before breaks and immediately after handling the product. Remove contaminated clothing and protective equipment before entering eating areas. Wash thoroughly after handling.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance	: liquid
Color	: various
Odor	: ether-like
Odor Threshold	: No data available
pH	: Not applicable
Melting point/ range / Freezing point	: No data available
Boiling point/boiling range	: No data available
Flash point	: 266 °F / 130 °C (Method: closed cup)
Evaporation rate	: No data available
Flammability (solid, gas)	: No data available
Upper explosion limit / Upper flammability limit	: No data available
Lower explosion limit / Lower flammability limit	: No data available
Vapor pressure	: 0.01 hpa
Relative vapor density	: No data available



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

Density	:	ca. 1.5 g/cm ³ (73 °F / 23 °C)
Solubility(ies)		
Water solubility	:	soluble
Solubility in other solvents	:	No data available
Partition coefficient: n-octanol/water	:	No data available
Autoignition temperature	:	No data available
Decomposition temperature	:	No data available
Viscosity		
Viscosity, dynamic	:	No data available
Viscosity, kinematic	:	> 20.5 mm ² /s (104 °F / 40 °C)
Explosive properties	:	No data available
Oxidizing properties	:	No data available
Volatile organic compounds (VOC) content	:	43 g/l Sikafloor®-264 Part A + Sikafloor®-161/264 Part B
		35 g/l Sikafloor®-264 Part A + Sikafloor®-264 Thixo Lite Part B
		12 g/l Sikafloor®-264 Part A + Sikafloor®-264 FS Part B

SECTION 10. STABILITY AND REACTIVITY

Reactivity	:	No dangerous reaction known under conditions of normal use.
Chemical stability	:	The product is chemically stable.
Possibility of hazardous reactions	:	Stable under recommended storage conditions.
Conditions to avoid	:	No data available
Incompatible materials	:	No data available
Hazardous decomposition products	:	No decomposition if stored and applied as directed.



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

SECTION 11. TOXICOLOGICAL INFORMATION

Acute toxicity

Not classified due to lack of data.

Components:

bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight $\leq$ 700):

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

Acute dermal toxicity : LD50 Dermal (Rabbit): > 20,000 mg/kg

bisphenol-F-(epichlorhydrin) epoxy resin:

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

P-tert-butylphenyl-1-(2,3-epoxy)propyl ether:

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

Acute inhalation toxicity : LC50 (Rat): 3,466 mg/l
Exposure time: 4 h
Test atmosphere: dust/mist

Acute dermal toxicity : LD50 Dermal (Rabbit): 6,000 mg/kg

Skin corrosion/irritation

Causes skin irritation.

Serious eye damage/eye irritation

Causes serious eye irritation.

Respiratory or skin sensitization

Skin sensitization

May cause an allergic skin reaction.

Respiratory sensitization

Not classified due to lack of data.

Germ cell mutagenicity

Not classified due to lack of data.

Carcinogenicity

May cause cancer by inhalation.

IARC	Group 1: Carcinogenic to humans	
	Quartz (SiO ₂)	14808-60-7
	(Silica dust, crystalline)	
	Group 2B: Possibly carcinogenic to humans	
	Titanium dioxide (> 10 µm)	13463-67-7
	Group 2B: Possibly carcinogenic to humans	



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

	Carbon black	1333-86-4
OSHA	OSHA specifically regulated carcinogen Quartz (SiO ₂) (crystalline silica)	14808-60-7
NTP	Known to be human carcinogen Quartz (SiO ₂) (Silica, Crystalline (Respirable Size))	14808-60-7

Reproductive toxicity

May damage fertility or the unborn child.

STOT-single exposure

May cause respiratory irritation.

STOT-repeated exposure

Causes damage to organs (Lungs) through prolonged or repeated exposure.

Once sensitized, a severe allergic reaction may occur when subsequently exposed to very low levels.

Aspiration toxicity

Not classified due to lack of data.

Further information

Product:

Remarks : Carbon black (1333-86-4)
Animal Toxicity:
 Rat, oral, duration 2 year
 Effect: no tumors

 Mouse, oral, duration 2 years
 Effect: no tumors
 Mouse, dermal, duration 18 months
 Effect: no skin tumors
 Rat, inhalation, duration 2 years
 Target organ: lungs
 Effect: inflammation, fibrosis, tumors
 Note: Tumors in the rat lung are considered to be related to the "particle overload phenomenon" rather than to a specific chemical effect of carbon black itself in the lung. These effects in rats have been reported in many studies on other poorly soluble inorganic particles and appear to be rat specific. Tumors have not been observed in other species (i.e., mouse and hamster) for carbon black or other poorly soluble particles under similar circumstances and study conditions.
 Mortality studies (human data): A study on carbon black production workers in the UK (Sorahan, 2001) found an increased risk of lung cancer in two of the five plant studied; however, the increase was not related to the dose of carbon black. Thus, the authors did not consider the increased risk in



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

lung cancer to be due to carbon black exposure. A German study of carbon black workers at one plant (Morfeld, 2006; Buechte, 2006) found a similar increase in lung cancer risk but, like the Sorohan, 2001 (UK study) found no association with carbon black exposure. A large US study of 18 plants showed a reduction in lung cancer risk in carbon black production workers (DEll, 2006). Based upon these studies, the February 2006 Working Group at the International Agency for Research on Cancer (IARC) concluded that the human evidence for carcinogenicity was inadequate (IARC, 2010). Since the IARC evaluation of carbon black, Sorahan and Harrington (2007) have re-analyzed the UK study data using an alternative exposure hypothesis and found a positive association with carbon black exposure in two of the five plants. The same exposure hypothesis was applied by Morfeld and McCunney (2009) to the German cohort; in contrast, they found no association between carbon black exposure and lung cancer risk and, thus, no support for the alternative exposure hypothesis used by Sorahan and Harrington. Overall, as a result of these detailed investigations, no causative link between carbon black exposure and cancer risk in humans has been demonstrated.

IARC CANCER CLASSIFICATION: In 2006 IARC re-affirmed its 1995 finding that there is "inadequate evidence" from human health studies to assess whether carbon black causes cancer in humans. IARC concluded that there is "sufficient evidence" in experimental animal studies for the carcinogenicity of carbon black. IARC's overall evaluation is that carbon black is "possibly carcinogenic to humans" (Group 2B). This conclusion was based on IARC's guidelines, which generally require such a classification if one species exhibits carcinogenicity in two or more animal studies (IARC, 2010).

Solvent extracts of carbon black were used in one study of rats in which skin tumors were found after dermal application and several studies of mice in which sarcomas were found following subcutaneous injection. IARC concluded that there was "sufficient evidence" that carbon black extracts can cause cancer in animals (Group 2B).

ICGIH CANCER CLASSIFICATION: Confirmed Animal Carcinogen with Unknown Relevance to Humans (Category A3 Carcinogen).

ASSESSMENT: Applying the guidelines of self-classification under the Globally Harmonized System of Classification and Labeling of Chemicals, carbon black is not classified as a carcinogen. Lung tumors are induced in rats as a result of repeated exposure to inert, poorly soluble particles like carbon black and other poorly soluble particles. Rats tumors are a result of a secondary non-genotoxic mechanism that has questionable relevance for classification in humans. In support



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

of this opinion, the CLP Guidance for Specific Target Organ Toxicity - Repeated Exposure (STOT-RE), cites lung overload under mechanisms not relevant to humans. Human health studies show that exposure to carbon black does not increase the risk to carcinogenicity.

Titanium dioxide (13463-67-7)

In lifetime inhalation studies of rats, airborne respirable-size titanium dioxide particles have shown to cause an increase in lung tumors at concentrations associated with substantial particle lung burdens and consequential pulmonary overload and inflammation. The potential for these adverse health effects appears to be closely related to the particle size and the amount of the exposed surface area that comes into contact with the lung. However, tests with other laboratory animals such as mice and hamsters, indicate that rats are significantly more susceptible to the pulmonary overload and inflammation that causes lung cancer. Epidemiological studies do not suggest an increased risk of cancer in humans from occupational exposure to titanium dioxide. Titanium dioxide has been characterized by IARC as possibly carcinogenic to humans (Group 2B) through inhalation (not ingestion). It has not been characterized as a potential carcinogen by either NTP or OSHA.

Quartz (14808-60-7): This classification is relevant when exposed to Quartz (silicon dioxide) in dust or powder form only, including cured product that is subject to sanding, grinding, cutting, or other surface preparation activities.

SECTION 12. ECOLOGICAL INFORMATION

Ecotoxicity

Components:

bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700):

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 2 mg/l
Exposure time: 96 h

Toxicity to daphnia and other : EC50 (Daphnia magna (Water flea)): 1.8 mg/l
aquatic invertebrates Exposure time: 48 h

Persistence and degradability

No data available

Bioaccumulative potential

No data available



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

Mobility in soil

No data available

Other adverse effects

Product:

Additional ecological information : Do not empty into drains; dispose of this material and its container in a safe way.
Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.
Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.
May be harmful to the environment if released in large quantities.
Water polluting material.

SECTION 13. DISPOSAL CONSIDERATIONS

Disposal methods

Waste from residues : Disposal of this product, solutions and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements.

Contaminated packaging : Empty containers should be taken to an approved waste handling site for recycling or disposal.

SECTION 14. TRANSPORT INFORMATION

International Regulations

IATA-DGR

UN/ID No. : UN 3082
Proper shipping name : Environmentally hazardous substance, liquid, n.o.s. (epoxy resin)
Class : 9
Packing group : III
Labels : Miscellaneous
Packing instruction (cargo aircraft) : 964
Packing instruction (passenger aircraft) : 964
Environmentally hazardous : yes

IMDG-Code

UN number : UN 3082
Proper shipping name : ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (epoxy resin)



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

Class : 9
Packing group : III
Labels : 9
EmS Code : F-A, S-F
Marine pollutant : yes

Domestic regulation

49 CFR Road

Not regulated as a dangerous good

DOT: As per 49 CFR 171.4, Non-bulk materials (<119 Gal) are exempt from being classified as a Marine Pollutant.

Special precautions for user

The transport classification(s) provided herein are for informational purposes only, and solely based upon the properties of the unpackaged material as it is described within this Safety Data Sheet. Transportation classifications may vary by mode of transportation, package sizes, and variations in regional or country regulations.

SECTION 15. REGULATORY INFORMATION

TSCA list : All chemical substances in this product are either listed as active on the TSCA Inventory or are in compliance with a TSCA Inventory exemption.

No substances are subject to a Significant New Use Rule.

No substances are subject to TSCA 12(b) export notification requirements.

CERCLA Reportable Quantity

Listed substances in the product are at low enough levels to not be expected to exceed the RQ

SARA 304 Extremely Hazardous Substances Reportable Quantity

Listed substances in the product are at low enough levels to not be expected to exceed the RQ

SARA 302 Extremely Hazardous Substances Threshold Planning Quantity

This material does not contain any components with a section 302 EHS TPQ.

SARA 311/312 Hazards : Respiratory or skin sensitization
Carcinogenicity
Reproductive toxicity
Specific target organ toxicity (single or repeated exposure)
Skin corrosion or irritation
Serious eye damage or eye irritation

SARA 313 : This material does not contain any chemical components with known CAS numbers that exceed the threshold (De Minimis) reporting levels established by SARA Title III, Section 313.



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

Clean Air Act

This product does not contain any hazardous air pollutants (HAP), as defined by the U.S. Clean Air Act Section 112 (40 CFR 61).

California Prop. 65

⚠ WARNING: This product can expose you to chemicals including Quartz (SiO₂) >5µm, which is known to the State of California to cause cancer, and toluene, which is known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

SECTION 16. OTHER INFORMATION

Full text of other abbreviations

ACGIH	:	USA. ACGIH Threshold Limit Values (TLV)
OSHA CARC	:	OSHA Specifically Regulated Chemicals/Carcinogens
OSHA P0	:	USA. Table Z-1-A Limits for Air Contaminants (1989 vacated values)
OSHA Z-1	:	USA. Occupational Exposure Limits (OSHA) - Table Z-1 Limits for Air Contaminants
OSHA Z-3	:	USA. Occupational Exposure Limits (OSHA) - Table Z-3 Mineral Dusts
ACGIH / TWA	:	8-hour, time-weighted average
OSHA CARC / PEL	:	Permissible exposure limit (PEL)
OSHA P0 / TWA	:	8-hour time weighted average
OSHA Z-1 / TWA	:	8-hour time weighted average
OSHA Z-3 / TWA	:	8-hour time weighted average

Notes to Reader

The information contained in this Safety Data Sheet applies only to the actual Sika Corporation ("Sika") product identified and described herein. This information is not intended to address, nor does it address the use or application of the identified Sika product in combination with any other material, product or process. All of the information set forth herein is based on technical data regarding the identified product that Sika believes to be reliable as of the date hereof. Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's current Product Data Sheet, product label and Safety Data Sheet for each Sika product, which are available at web site and/or telephone number listed in Section 1 of this SDS.

SIKA MAKES NO WARRANTIES EXPRESS OR IMPLIED AND ASSUMES NO LIABILITY ARISING FROM THIS INFORMATION OR ITS USE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES AND SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

All sales of Sika products are subject to its current terms and conditions of sale available at www.sikausa.com or 201-933-8800.



Sikafloor®-264 Part A

Revision Date 02/04/2025

Print Date 02/04/2025

Revision Date 02/04/2025

100000006275
US / Z8



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

SECTION 1. IDENTIFICATION

Product name : Sikafloor®-161/264 Part B

Company name : Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
USA
www.sikausa.com

Telephone : (201) 933-8800

Telefax : (201) 804-1076

E-mail address : ehs@sika-corp.com

Emergency telephone : CHEMTREC: 800-424-9300
INTERNATIONAL: +1-703-527-3887

Recommended use of the chemical and restrictions on use : For further information, refer to product data sheet.

SECTION 2. HAZARDS IDENTIFICATION

GHS classification in accordance with the OSHA Hazard Communication Standard (29 CFR 1910.1200)

Acute toxicity (Oral) : Category 4

Skin corrosion : Sub-category 1B

Serious eye damage : Category 1

Skin sensitization : Category 1

Reproductive toxicity : Category 2

Other hazards

Intentional misuse by deliberate concentration and inhalation of vapor may be harmful or fatal.

GHS label elements

Hazard pictograms :





Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

Signal Word	: Danger
Hazard Statements	: H302 Harmful if swallowed. H314 Causes severe skin burns and eye damage. H317 May cause an allergic skin reaction. H361 Suspected of damaging fertility or the unborn child.
Supplemental Hazard Statements	: Corrosive to the respiratory tract.
Precautionary Statements	: Prevention: P201 Obtain special instructions before use. P202 Do not handle until all safety precautions have been read and understood. P261 Avoid breathing mist or vapors. P264 Wash skin thoroughly after handling. P270 Do not eat, drink or smoke when using this product. P272 Contaminated work clothing must not be allowed out of the workplace. P280 Wear protective gloves/ protective clothing/ eye protection/ face protection/ hearing protection. Response: P301 + P312 + P330 IF SWALLOWED: Call a POISON CENTER/ doctor if you feel unwell. Rinse mouth. P302 + P352 IF ON SKIN: Wash with plenty of water. P305 + P351 + P338 + P310 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a POISON CENTER/ doctor. P308 + P313 IF exposed or concerned: Get medical advice/ attention. P333 + P313 If skin irritation or rash occurs: Get medical advice/ attention. P362 + P364 Take off contaminated clothing and wash it before reuse. Storage: P405 Store locked up. Disposal: P501 Dispose of contents/ container to an approved waste disposal plant.

Additional Labeling

There are no ingredients with unknown acute toxicity used in a mixture at a concentration $\geq 1\%$.



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS

Mixtures

Components

Chemical name	CAS No./Unique ID	Classification	Concentration (% w/w)
Benzyl alcohol	100-51-6	Acute Tox. 4; H302 Eye Irrit. 2A; H319 Skin Sens. 1B; H317	>= 45 - <= 70
Adduct IXA (Epoxy Amine Adduct)	ACCNO: 252712	Acute Tox. 4; H302 Skin Sens. 1; H317	>= 10 - <= 30
Isophoronediamine	2855-13-2	Acute Tox. 4; H302 Skin Corr. 1B; H314 Eye Dam. 1; H318 Skin Sens. 1A; H317	>= 10 - <= 30
m-phenylenebis(methylamine)	1477-55-0	Acute Tox. 4; H302 Acute Tox. 4; H332 Skin Corr. 1B; H314 Skin Sens. 1B; H317	>= 7 - <= 13
Phenol, 4-nonyl, branched	84852-15-3	Acute Tox. 4; H302 Skin Corr. 1B; H314 Eye Dam. 1; H318 Repr. 2; H361	>= 3 - <= 7
2,4,6-tris(dimethylaminomethyl)phenol	90-72-2	Acute Tox. 4; H302 Skin Irrit. 2; H315 Eye Irrit. 2A; H319	>= 3 - <= 7

Actual concentration is withheld as a trade secret

SECTION 4. FIRST AID MEASURES

- General advice : Move out of dangerous area.
Consult a physician.
Show this material safety data sheet to the doctor in attendance.
- If inhaled : Move to fresh air.
Consult a physician after significant exposure.
- In case of skin contact : Take off contaminated clothing and shoes immediately.
Wash off with soap and plenty of water.
Immediate medical treatment is necessary as untreated wounds from corrosion of the skin heal slowly and with difficulty.
- In case of eye contact : Small amounts splashed into eyes can cause irreversible tissue damage and blindness.
In the case of contact with eyes, rinse immediately with plenty of water and seek medical advice.



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

- Continue rinsing eyes during transport to hospital.
Remove contact lenses.
Keep eye wide open while rinsing.
- If swallowed : Clean mouth with water and drink afterwards plenty of water.
Do not induce vomiting without medical advice.
Do not give milk or alcoholic beverages.
Never give anything by mouth to an unconscious person.
Take victim immediately to hospital.
- Most important symptoms and effects, both acute and delayed : Gastrointestinal discomfort
Allergic reactions
Dermatitis
Health injuries may be delayed.
corrosive effects
sensitizing effects
Harmful if swallowed.
May cause an allergic skin reaction.
Causes serious eye damage.
Suspected of damaging fertility or the unborn child.
Causes severe burns.
Corrosive to the respiratory tract.
- Notes to physician : Treat symptomatically.

SECTION 5. FIRE-FIGHTING MEASURES

- Suitable extinguishing media : Use extinguishing measures that are appropriate to local circumstances and the surrounding environment.
- Further information : Collect contaminated fire extinguishing water separately. This must not be discharged into drains.
Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.
- Special protective equipment for fire-fighters : In the event of fire, wear self-contained breathing apparatus.

SECTION 6. ACCIDENTAL RELEASE MEASURES

- Personal precautions, protective equipment and emergency procedures : Use personal protective equipment.
Deny access to unprotected persons.
- Environmental precautions : Do not flush into surface water or sanitary sewer system.
If the product contaminates rivers and lakes or drains inform respective authorities.
Local authorities should be advised if significant spillages cannot be contained.



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

Methods and materials for containment and cleaning up : Soak up with inert absorbent material (e.g. sand, silica gel, acid binder, universal binder, sawdust).
Keep in suitable, closed containers for disposal.

SECTION 7. HANDLING AND STORAGE

Advice on protection against fire and explosion : Normal measures for preventive fire protection.

Advice on safe handling : Avoid exceeding the given occupational exposure limits (see section 8).
Do not get in eyes, on skin, or on clothing.
For personal protection see section 8.
Persons with a history of skin sensitization problems or asthma, allergies, chronic or recurrent respiratory disease should not be employed in any process in which this mixture is being used.
Smoking, eating and drinking should be prohibited in the application area.
Follow standard hygiene measures when handling chemical products.

Conditions for safe storage : Store in original container.
Keep container tightly closed in a dry and well-ventilated place.
Containers which are opened must be carefully resealed and kept upright to prevent leakage.
Observe label precautions.
Store in accordance with local regulations.

Materials to avoid : Explosives
Oxidizing agents
Poisonous gases
Dangerous when wet
Flammable solids
Organic peroxides
Poisonous liquids
Spontaneously Combustible Substances

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Ingredients with workplace control parameters

Components	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
m-phenylenebis(methylamine)	1477-55-0	C	0.018 ppm	ACGIH
		C	0.1 mg/m3	OSHA P0



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

The above constituents are the only constituents of the product which have a PEL, TLV or other recommended exposure limit. At this time, the other constituents have no known exposure limits.

Engineering measures : Use of adequate ventilation should be sufficient to control worker exposure to airborne contaminants. If the use of this product generates dust, fumes, gas, vapor or mist, use process enclosures, local exhaust ventilation or other engineering controls to keep worker exposure below any recommended or statutory limits.

Personal protective equipment

Respiratory protection : Use a properly fitted NIOSH approved air-purifying or air-fed respirator complying with an approved standard if a risk assessment indicates this is necessary.

The filter class for the respirator must be suitable for the maximum expected contaminant concentration (gas/vapor/aerosol/particulates) that may arise when handling the product. If this concentration is exceeded, self-contained breathing apparatus must be used.

Hand protection : Chemical-resistant, impervious gloves complying with an approved standard should be worn at all times when handling chemical products if a risk assessment indicates this is necessary.

Eye protection : Safety eyewear complying with an approved standard should be used when a risk assessment indicates this is necessary.

Skin and body protection : Choose body protection in relation to its type, to the concentration and amount of dangerous substances, and to the specific work-place.

Hygiene measures : Avoid contact with skin, eyes and clothing.
Wash hands before breaks and immediately after handling the product.
Remove contaminated clothing and protective equipment before entering eating areas.
Wash thoroughly after handling.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance : liquid

Color : amber

Odor : amine-like

Odor Threshold : No data available



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

pH	:	Not applicable
Melting point/ range / Freezing point	:	No data available
Boiling point/boiling range	:	No data available
Flash point	:	> 199.99 °F / > 93.33 °C (Method: closed cup)
Evaporation rate	:	No data available
Flammability (solid, gas)	:	No data available
Upper explosion limit / Upper flammability limit	:	No data available
Lower explosion limit / Lower flammability limit	:	No data available
Vapor pressure	:	0.07 hpa
Relative vapor density	:	No data available
Density	:	ca. 1.03 g/cm ³ (73 °F / 23 °C)
Solubility(ies)		
Water solubility	:	partly soluble
Solubility in other solvents	:	No data available
Partition coefficient: n-octanol/water	:	No data available
Autoignition temperature	:	No data available
Decomposition temperature	:	No data available
Viscosity		
Viscosity, dynamic	:	No data available
Viscosity, kinematic	:	ca. > 20.5 mm ² /s (104 °F / 40 °C)
Explosive properties	:	No data available
Oxidizing properties	:	No data available
Volatile organic compounds (VOC) content	:	62 g/l Sikafloor®-161 Part A + Sikafloor®-161/264 Part B Combined. 43 g/l Sikafloor®-264 Part A + Sikafloor®-161/264 Part B Combined.



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

35 g/l
Sikafloor®-264 ECF Part A + Sikafloor®-161/264 Part B
Combined.

SECTION 10. STABILITY AND REACTIVITY

Reactivity	: No dangerous reaction known under conditions of normal use.
Chemical stability	: The product is chemically stable.
Possibility of hazardous reactions	: Stable under recommended storage conditions.
Conditions to avoid	: No data available
Incompatible materials	: No data available
Hazardous decomposition products	: No decomposition if stored and applied as directed.

SECTION 11. TOXICOLOGICAL INFORMATION

Acute toxicity

Harmful if swallowed.

Components:

Benzyl alcohol:

Acute oral toxicity	: LD50 Oral (Rat): 1,200 mg/kg
Acute inhalation toxicity	: LC50 (Rat): > 4.178 mg/l Exposure time: 4 h Test atmosphere: dust/mist

Isophoronediamine:

Acute oral toxicity	: LD50 Oral (Rat): 1,030 mg/kg
Acute inhalation toxicity	: LC50 (Rat): > 5 mg/l Exposure time: 4 h Test atmosphere: dust/mist
Acute dermal toxicity	: LD50 (Rabbit): > 2,000 - 5,000 mg/kg

m-phenylenebis(methylamine):

Acute oral toxicity	: LD50 Oral (Rat): 930 mg/kg
---------------------	------------------------------



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

Acute inhalation toxicity : LC50 (Rat): 1.34 mg/l
Exposure time: 4 h
Test atmosphere: dust/mist
Assessment: Corrosive to the respiratory tract.

Acute dermal toxicity : LD50 Dermal (Rat): > 3,100 mg/kg

Phenol, 4-nonyl, branched:

Acute oral toxicity : LD50 Oral (Rat): 1,412 mg/kg

Acute dermal toxicity : LD50 Dermal (Rabbit): 3,160 mg/kg

2,4,6-tris(dimethylaminomethyl)phenol:

Acute oral toxicity : LD50 Oral (Rat): 2,169 mg/kg

Skin corrosion/irritation

Causes severe burns.

Components:

2,4,6-tris(dimethylaminomethyl)phenol:

Species : Rabbit
Assessment : Corrosive
Method : OECD Test Guideline 404

Serious eye damage/eye irritation

Causes serious eye damage.

Components:

2,4,6-tris(dimethylaminomethyl)phenol:

Species : Rabbit
Assessment : Causes serious eye damage.

Respiratory or skin sensitization

Skin sensitization

May cause an allergic skin reaction.

Respiratory sensitization

Not classified due to lack of data.

Germ cell mutagenicity

Not classified due to lack of data.

Carcinogenicity

Not classified due to lack of data.

IARC Not applicable



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

OSHA Not applicable

NTP Not applicable

Reproductive toxicity

Suspected of damaging fertility or the unborn child.

STOT-single exposure

Corrosive to the respiratory tract.

STOT-repeated exposure

Not classified due to lack of data.

Once sensitized, a severe allergic reaction may occur when subsequently exposed to very low levels.

Aspiration toxicity

Not classified due to lack of data.

SECTION 12. ECOLOGICAL INFORMATION

Ecotoxicity

Components:

Benzyl alcohol:

Toxicity to fish : LC50 (Fish): > 100 mg/l
Exposure time: 96 h

Toxicity to daphnia and other : EC50 (Daphnia magna (Water flea)): > 100 mg/l
aquatic invertebrates Exposure time: 48 h

Isophoronediamine:

Toxicity to algae/aquatic : ErC50 (Desmodesmus subspicatus (green algae)): > 10 - 100
plants mg/l

NOEC (Desmodesmus subspicatus (green algae)): 1.5 mg/l

m-phenylenebis(methylamine):

Toxicity to fish : LC50 (Oryzias latipes (Japanese medaka)): > 10 - 100 mg/l
Exposure time: 96 h

Toxicity to daphnia and other : EC50 (Daphnia magna (Water flea)): > 10 - 100 mg/l
aquatic invertebrates Exposure time: 48 h

Phenol, 4-nonyl, branched:

Persistence and degradability

No data available



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

Bioaccumulative potential

No data available

Mobility in soil

No data available

Other adverse effects

Product:

Additional ecological information : Do not empty into drains; dispose of this material and its container in a safe way.
Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.
Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.
May be harmful to the environment if released in large quantities.
Water polluting material.

SECTION 13. DISPOSAL CONSIDERATIONS

Disposal methods

Waste from residues : Disposal of this product, solutions and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements.

Contaminated packaging : Empty containers should be taken to an approved waste handling site for recycling or disposal.

SECTION 14. TRANSPORT INFORMATION

International Regulations

IATA-DGR

UN/ID No. : UN 3066
Proper shipping name : Paint
Class : 8
Packing group : II
Labels : Corrosive
Packing instruction (cargo aircraft) : 855
Packing instruction (passenger aircraft) : 851
Environmentally hazardous : yes

IMDG-Code

UN number : UN 3066
Proper shipping name : PAINT



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

(phenol, dodecyl-, branched)
Class : 8
Packing group : II
Labels : 8
EmS Code : F-A, S-B
Marine pollutant : yes

Domestic regulation

49 CFR Road

UN/ID/NA number : UN 3066
Proper shipping name : Paint
Class : 8
Packing group : II
Labels : CORROSIVE
ERG Code : 153
Marine pollutant : yes

Special precautions for user

The transport classification(s) provided herein are for informational purposes only, and solely based upon the properties of the unpackaged material as it is described within this Safety Data Sheet. Transportation classifications may vary by mode of transportation, package sizes, and variations in regional or country regulations.

SECTION 15. REGULATORY INFORMATION

TSCA list : All chemical substances in this product are either listed on the TSCA Inventory or are in compliance with a TSCA Inventory exemption.

The following substance(s) is/are subject to a Significant New Use Rule:

Phenol, 4-nonyl, branched	84852-15-3	See 40 CFR § 721.10765; Proposed Rule
---------------------------	------------	---------------------------------------

The following substance(s) is/are subject to TSCA 12(b) export notification requirements:

Phenol, 4-nonyl, branched	84852-15-3
---------------------------	------------

CERCLA Reportable Quantity

Listed substances in the product are at low enough levels to not be expected to exceed the RQ

SARA 304 Extremely Hazardous Substances Reportable Quantity

Listed substances in the product are at low enough levels to not be expected to exceed the RQ

SARA 302 Extremely Hazardous Substances Threshold Planning Quantity

This material does not contain any components with a section 302 EHS TPQ.

SARA 311/312 Hazards : Acute toxicity (any route of exposure)
Respiratory or skin sensitization
Reproductive toxicity
Skin corrosion or irritation
Serious eye damage or eye irritation



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

SARA 313 : The following components are subject to reporting levels established by SARA Title III, Section 313:

Phenol, 4-nonyl, 84852-15-3 $\geq 1 - < 5 \%$
branched

Clean Air Act

This product does not contain any hazardous air pollutants (HAP), as defined by the U.S. Clean Air Act Section 112 (40 CFR 61).

California Prop. 65

⚠ WARNING: This product can expose you to chemicals including α -chlorotoluene, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov.

SECTION 16. OTHER INFORMATION

Full text of other abbreviations

ACGIH	: USA. ACGIH Threshold Limit Values (TLV)
OSHA P0	: USA. Table Z-1-A Limits for Air Contaminants (1989 vacated values)
ACGIH / C	: Ceiling limit
OSHA P0 / C	: Ceiling limit

Notes to Reader

The information contained in this Safety Data Sheet applies only to the actual Sika Corporation ("Sika") product identified and described herein. This information is not intended to address, nor does it address the use or application of the identified Sika product in combination with any other material, product or process. All of the information set forth herein is based on technical data regarding the identified product that Sika believes to be reliable as of the date hereof. Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's current Product Data Sheet, product label and Safety Data Sheet for each Sika product, which are available at web site and/or telephone number listed in Section 1 of this SDS.

SIKA MAKES NO WARRANTIES EXPRESS OR IMPLIED AND ASSUMES NO LIABILITY ARISING FROM THIS INFORMATION OR ITS USE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES AND SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

All sales of Sika products are subject to its current terms and conditions of sale available at www.sikausa.com or 201-933-8800.

Revision Date 03/28/2025



Sikafloor®-161/264 Part B

Revision Date 03/28/2025

Print Date 03/28/2025

100000005304
US / Z8



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

SECTION 1. IDENTIFICATION

Product name : Sikafloor® 340 Part A

Company name : Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
USA
www.sikausa.com

Telephone : (201) 933-8800

Telefax : (201) 804-1076

E-mail address : ehs@sika-corp.com

Emergency telephone : CHEMTREC: 800-424-9300
INTERNATIONAL: +1-703-527-3887

Recommended use of the chemical and restrictions on use : For further information, refer to product data sheet.

SECTION 2. HAZARDS IDENTIFICATION

GHS classification in accordance with the OSHA Hazard Communication Standard (29 CFR 1910.1200)

Flammable liquids : Category 3

Reproductive toxicity : Category 1B

Specific target organ toxicity - single exposure : Category 3 (Central nervous system)

GHS label elements

Hazard pictograms : 

Signal Word : Danger

Hazard Statements : H226 Flammable liquid and vapor.
H336 May cause drowsiness or dizziness.
H360 May damage fertility or the unborn child.

Precautionary Statements : **Prevention:**



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

P201 Obtain special instructions before use.
P202 Do not handle until all safety precautions have been read and understood.
P210 Keep away from heat/ sparks/ open flames/ hot surfaces. No smoking.
P233 Keep container tightly closed.
P240 Ground/bond container and receiving equipment.
P241 Use explosion-proof electrical/ ventilating/ lighting/ equipment.
P242 Use only non-sparking tools.
P243 Take precautionary measures against static discharge.
P261 Avoid breathing mist or vapors.
P271 Use only outdoors or in a well-ventilated area.
P280 Wear protective gloves/ protective clothing/ eye protection/ face protection.

Response:

P303 + P361 + P353 IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin with water/ shower.
P304 + P340 + P312 IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a POISON CENTER/ doctor if you feel unwell.
P308 + P313 IF exposed or concerned: Get medical advice/ attention.
P370 + P378 In case of fire: Use dry sand, dry chemical or alcohol-resistant foam to extinguish.

Storage:

P403 + P233 Store in a well-ventilated place. Keep container tightly closed.
P403 + P235 Store in a well-ventilated place. Keep cool.
P405 Store locked up.

Disposal:

P501 Dispose of contents/ container to an approved waste disposal plant.

Additional Labeling

There are no ingredients with unknown acute toxicity used in a mixture at a concentration $\geq 1\%$.

Other hazards

None known.

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS

Mixtures

Components

Chemical name	CAS-No.	Classification	Concentration (% w/w)
2-methoxy-1-methylethyl acetate	108-65-6	Flam. Liq. 3; H226	$\geq 30 - < 50$



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

tert-butyl acetate	540-88-5	STOT SE 3; H336 Flam. Liq. 2; H225 Acute Tox. 4; H332 STOT SE 3; H335, H336	>= 5 - < 10
2-methoxypropyl acetate	70657-70-4	Flam. Liq. 3; H226 Repr. 1B; H360 STOT SE 3; H335	>= 0.1 - < 1

Actual concentration is withheld as a trade secret

SECTION 4. FIRST AID MEASURES

- General advice : Move out of dangerous area.
Consult a physician.
Show this material safety data sheet to the doctor in attendance.
- If inhaled : Move to fresh air.
Consult a physician after significant exposure.
- In case of skin contact : Take off contaminated clothing and shoes immediately.
Wash off with soap and plenty of water.
If symptoms persist, call a physician.
- In case of eye contact : Remove contact lenses.
Keep eye wide open while rinsing.
If eye irritation persists, consult a specialist.
- If swallowed : Clean mouth with water and drink afterwards plenty of water.
Do not induce vomiting without medical advice.
Do not give milk or alcoholic beverages.
Never give anything by mouth to an unconscious person.
- Most important symptoms and effects, both acute and delayed : Respiratory disorder
Loss of balance
Vertigo
toxic effects for reproduction
May cause drowsiness or dizziness.
May damage fertility or the unborn child.
- Notes to physician : Treat symptomatically.

SECTION 5. FIRE-FIGHTING MEASURES

- Suitable extinguishing media : Alcohol-resistant foam
Carbon dioxide (CO₂)
Dry chemical
- Unsuitable extinguishing media : Water
- Further information : Use water spray to cool unopened containers.



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

Collect contaminated fire extinguishing water separately. This must not be discharged into drains.
Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.

Special protective equipment : In the event of fire, wear self-contained breathing apparatus.
for fire-fighters

SECTION 6. ACCIDENTAL RELEASE MEASURES

- Personal precautions, protective equipment and emergency procedures : Use personal protective equipment.
Remove all sources of ignition.
Deny access to unprotected persons.
Beware of vapors accumulating to form explosive concentrations. Vapors can accumulate in low areas.
- Environmental precautions : Prevent product from entering drains.
If the product contaminates rivers and lakes or drains inform respective authorities.
Local authorities should be advised if significant spillages cannot be contained.
- Methods and materials for containment and cleaning up : Contain spillage, and then collect with non-combustible absorbent material, (e.g. sand, earth, diatomaceous earth, vermiculite) and place in container for disposal according to local / national regulations (see section 13).

SECTION 7. HANDLING AND STORAGE

- Advice on protection against fire and explosion : Use explosion-proof equipment.
Keep away from heat/ sparks/ open flames/ hot surfaces. No smoking.
Take precautionary measures against electrostatic discharges.
- Advice on safe handling : Do not breathe vapors or spray mist.
Avoid exceeding the given occupational exposure limits (see section 8).
Do not get in eyes, on skin, or on clothing.
For personal protection see section 8.
Smoking, eating and drinking should be prohibited in the application area.
Take precautionary measures against static discharge.
Open drum carefully as content may be under pressure.
Pregnant women or women of child-bearing age should not be exposed to this product.
Take necessary action to avoid static electricity discharge (which might cause ignition of organic vapors).
Follow standard hygiene measures when handling chemical products.



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

Conditions for safe storage : Store in original container.
Keep in a well-ventilated place.
Containers which are opened must be carefully resealed and kept upright to prevent leakage.
Observe label precautions.
Store in accordance with local regulations.

Materials to avoid : Explosives
Oxidizing agents
Poisonous gases
Poisonous liquids

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Ingredients with workplace control parameters

Components	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
tert-butyl acetate	540-88-5	TWA	200 ppm 950 mg/m ³	OSHA Z-1
		TWA	200 ppm 950 mg/m ³	OSHA P0
		TWA	50 ppm	ACGIH
		STEL	150 ppm	ACGIH

The above constituents are the only constituents of the product which have a PEL, TLV or other recommended exposure limit. At this time, the other constituents have no known exposure limits.

Engineering measures : Use of adequate ventilation should be sufficient to control worker exposure to airborne contaminants. If the use of this product generates dust, fumes, gas, vapor or mist, use process enclosures, local exhaust ventilation or other engineering controls to keep worker exposure below any recommended or statutory limits.
The engineering controls also need to keep gas, vapor or dust concentrations below any lower explosive limits.

Personal protective equipment

Respiratory protection : Use a properly fitted NIOSH approved air-purifying or air-fed respirator complying with an approved standard if a risk assessment indicates this is necessary.

The filter class for the respirator must be suitable for the maximum expected contaminant concentration (gas/vapor/aerosol/particulates) that may arise when handling the product. If this concentration is exceeded, self-contained breathing apparatus must be used.



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

Hand protection	: Chemical-resistant, impervious gloves complying with an approved standard should be worn at all times when handling chemical products if a risk assessment indicates this is necessary.
Eye protection	: Safety eyewear complying with an approved standard should be used when a risk assessment indicates this is necessary.
Skin and body protection	: Choose body protection in relation to its type, to the concentration and amount of dangerous substances, and to the specific work-place.
Hygiene measures	: Avoid contact with skin, eyes and clothing. Wash hands before breaks and immediately after handling the product. Remove respiratory and skin/eye protection only after vapors have been cleared from the area. Remove contaminated clothing and protective equipment before entering eating areas.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance	: liquid
Color	: amber, clear
Odor	: characteristic
Odor Threshold	: No data available
pH	: Not applicable
Melting point/range / Freezing point	: No data available
Boiling point/boiling range	: No data available
Flash point	: 115 °F / 46 °C (Method: closed cup)
Evaporation rate	: No data available
Flammability (solid, gas)	: No data available
Upper explosion limit / Upper flammability limit	: 10.8 %(V)
Lower explosion limit / Lower flammability limit	: 1.5 %(V)
Vapor pressure	: 41 hpa



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

Relative vapor density	:	No data available
Density	:	ca. 1.04 g/cm ³ (73 °F / 23 °C)
Solubility(ies)		
Water solubility	:	partly soluble
Solubility in other solvents	:	No data available
Partition coefficient: n-octanol/water	:	No data available
Autoignition temperature	:	333 °C
Decomposition temperature	:	No data available
Viscosity		
Viscosity, dynamic	:	No data available
Viscosity, kinematic	:	ca. > 20.5 mm ² /s (104 °F / 40 °C)
Explosive properties	:	No data available
Oxidizing properties	:	No data available
Volatile organic compounds (VOC) content	:	279 g/l A+B Combined. With exempt solvent.
		282 g/l Sikafloor®-340 Part A + B + Sikafloor®-372 Urethane Accelerator Combined. With exempt solvent.

SECTION 10. STABILITY AND REACTIVITY

Reactivity	:	No dangerous reaction known under conditions of normal use.
Chemical stability	:	The product is chemically stable.
Possibility of hazardous reactions	:	Stable under recommended storage conditions. Vapors may form explosive mixture with air.
Conditions to avoid	:	Heat, flames and sparks.
Incompatible materials	:	No data available
Hazardous decomposition products	:	No decomposition if stored and applied as directed.



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

SECTION 11. TOXICOLOGICAL INFORMATION

Acute toxicity

Not classified due to lack of data.

Components:

2-methoxy-1-methylethyl acetate:

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

Acute dermal toxicity : LD50 Dermal (Rabbit): > 5,000 mg/kg

tert-butyl acetate:

Acute oral toxicity : LD50 Oral (Rat): 4,500 mg/kg

Skin corrosion/irritation

Not classified due to lack of data.

Serious eye damage/eye irritation

Not classified due to lack of data.

Respiratory or skin sensitization

Skin sensitization

Not classified due to lack of data.

Respiratory sensitization

Not classified due to lack of data.

Germ cell mutagenicity

Not classified due to lack of data.

Carcinogenicity

Not classified due to lack of data.

IARC Not applicable

OSHA Not applicable

NTP Not applicable

Reproductive toxicity

May damage fertility or the unborn child.

STOT-single exposure

May cause drowsiness or dizziness.

STOT-repeated exposure

Not classified due to lack of data.

Aspiration toxicity

Not classified due to lack of data.



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

SECTION 12. ECOLOGICAL INFORMATION

Ecotoxicity

No data available

Persistence and degradability

No data available

Bioaccumulative potential

No data available

Mobility in soil

No data available

Other adverse effects

Product:

Additional ecological information : Do not empty into drains; dispose of this material and its container in a safe way.
Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.

SECTION 13. DISPOSAL CONSIDERATIONS

Disposal methods

Waste from residues : Disposal of this product, solutions and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements.

Contaminated packaging : Empty containers should be taken to an approved waste handling site for recycling or disposal.

SECTION 14. TRANSPORT INFORMATION

International Regulations

IATA-DGR

UN/ID No. : UN 1263
Proper shipping name : Paint
Class : 3
Packing group : III
Labels : Flammable Liquids
Packing instruction (cargo aircraft) : 366
Packing instruction (passenger aircraft) : 355

IMDG-Code



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

UN number : UN 1263
Proper shipping name : PAINT
Class : 3
Packing group : III
Labels : 3
EmS Code : F-E, S-E
Marine pollutant : no

Domestic regulation

49 CFR

UN/ID/NA number : UN 1263
Proper shipping name : Paint
Class : 3
Packing group : III
Labels : FLAMMABLE LIQUID
ERG Code : 128
Marine pollutant : no

DOT: As per 49CFR 173.150 (f) Combustible Liquid Exception, Material is Not Regulated.
IMDG: For Limited Quantity special provisions reference IMDG Code Chapter 3.4

Special precautions for user

The transport classification(s) provided herein are for informational purposes only, and solely based upon the properties of the unpackaged material as it is described within this Safety Data Sheet. Transportation classifications may vary by mode of transportation, package sizes, and variations in regional or country regulations.

SECTION 15. REGULATORY INFORMATION

TSCA list : All chemical substances in this product are either listed as active on the TSCA Inventory or are in compliance with a TSCA Inventory exemption.

No substances are subject to a Significant New Use Rule.

No substances are subject to TSCA 12(b) export notification requirements.

CERCLA Reportable Quantity

Listed substances in the product are at low enough levels to not be expected to exceed the RQ

SARA 304 Extremely Hazardous Substances Reportable Quantity

This material does not contain any components with a section 304 EHS RQ.

SARA 302 Extremely Hazardous Substances Threshold Planning Quantity

This material does not contain any components with a section 302 EHS TPQ.

SARA 311/312 Hazards : Flammable (gases, aerosols, liquids, or solids)
Reproductive toxicity
Specific target organ toxicity (single or repeated exposure)



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

SARA 313 : This material does not contain any chemical components with known CAS numbers that exceed the threshold (De Minimis) reporting levels established by SARA Title III, Section 313.

Clean Air Act

This product does not contain any hazardous air pollutants (HAP), as defined by the U.S. Clean Air Act Section 112 (40 CFR 61).

California Prop. 65

⚠ WARNING: This product can expose you to chemicals including cumene, which is known to the State of California to cause cancer, and benzene, which is known to the State of California to cause birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov.

SECTION 16. OTHER INFORMATION

Full text of other abbreviations

ACGIH	:	USA. ACGIH Threshold Limit Values (TLV)
OSHA P0	:	USA. Table Z-1-A Limits for Air Contaminants (1989 vacated values)
OSHA Z-1	:	USA. Occupational Exposure Limits (OSHA) - Table Z-1 Limits for Air Contaminants
ACGIH / TWA	:	8-hour, time-weighted average
ACGIH / STEL	:	Short-term exposure limit
OSHA P0 / TWA	:	8-hour time weighted average
OSHA Z-1 / TWA	:	8-hour time weighted average

Notes to Reader

The information contained in this Safety Data Sheet applies only to the actual Sika Corporation ("Sika") product identified and described herein. This information is not intended to address, nor does it address the use or application of the identified Sika product in combination with any other material, product or process. All of the information set forth herein is based on technical data regarding the identified product that Sika believes to be reliable as of the date hereof. Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's current Product Data Sheet, product label and Safety Data Sheet for each Sika product, which are available at web site and/or telephone number listed in Section 1 of this SDS.

SIKA MAKES NO WARRANTIES EXPRESS OR IMPLIED AND ASSUMES NO LIABILITY ARISING FROM THIS INFORMATION OR ITS USE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES AND SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

All sales of Sika products are subject to its current terms and conditions of sale available at www.sikausa.com or 201-933-8800.

Revision Date 11/09/2023



Sikafloor® 340 Part A

Revision Date 11/09/2023

Print Date 11/09/2023

000000604945
US / Z8



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

SECTION 1. IDENTIFICATION

Product name : Sikafloor® 340 Part B

Company name : Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
USA
www.sikausa.com

Telephone : (201) 933-8800

Telefax : (201) 804-1076

E-mail address : ehs@sika-corp.com

Emergency telephone : CHEMTREC: 800-424-9300
INTERNATIONAL: +1-703-527-3887

Recommended use of the chemical and restrictions on use : For further information, refer to product data sheet.

SECTION 2. HAZARDS IDENTIFICATION

GHS classification in accordance with the OSHA Hazard Communication Standard (29 CFR 1910.1200)

Flammable liquids : Category 3

Acute toxicity (Inhalation) : Category 4

Respiratory sensitization : Category 1

Skin sensitization : Category 1

GHS label elements

Hazard pictograms :



Signal Word : Danger

Hazard Statements : H226 Flammable liquid and vapor.
H317 May cause an allergic skin reaction.
H332 Harmful if inhaled.
H334 May cause allergy or asthma symptoms or breathing difficulties if inhaled.



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

Precautionary Statements

:

Prevention:

P210 Keep away from heat/ sparks/ open flames/ hot surfaces.
No smoking.

P233 Keep container tightly closed.

P240 Ground/bond container and receiving equipment.

P241 Use explosion-proof electrical/ ventilating/ lighting/ equipment.

P242 Use only non-sparking tools.

P243 Take precautionary measures against static discharge.

P261 Avoid breathing mist or vapors.

P271 Use only outdoors or in a well-ventilated area.

P272 Contaminated work clothing must not be allowed out of the workplace.

P280 Wear protective gloves/ protective clothing/ eye protection/ face protection.

P284 Wear respiratory protection.

Response:

P303 + P361 + P353 IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin with water/ shower.

P304 + P340 + P312 IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a POISON CENTER/ doctor if you feel unwell.

P333 + P313 If skin irritation or rash occurs: Get medical advice/ attention.

P342 + P311 If experiencing respiratory symptoms: Call a POISON CENTER/ doctor.

P362 + P364 Take off contaminated clothing and wash it before reuse.

P370 + P378 In case of fire: Use dry sand, dry chemical or alcohol-resistant foam to extinguish.

Storage:

P403 + P235 Store in a well-ventilated place. Keep cool.

Disposal:

P501 Dispose of contents/ container to an approved waste disposal plant.

Additional Labeling

There are no ingredients with unknown acute toxicity used in a mixture at a concentration $\geq 1\%$.

Other hazards

Intentional misuse by deliberate concentration and inhalation of vapor may be harmful or fatal.



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS

Mixtures

Components

Chemical name	CAS-No.	Classification	Concentration (% w/w)
Aliphatic polyisocyanate	28182-81-2	Skin Sens. 1; H317	$\geq 90 - \leq 100$
solvent naphtha (petroleum), light arom.	64742-95-6	Flam. Liq. 3; H226 STOT SE 3; H335, H336 Asp. Tox. 1; H304	$\geq 5 - < 10$
hexamethylene-di-isocyanate	822-06-0	Acute Tox. 1; H330 Skin Irrit. 2; H315 Eye Irrit. 2A; H319 Resp. Sens. 1; H334 Skin Sens. 1; H317 STOT SE 3; H335	$\geq 0.1 - < 1$

Actual concentration is withheld as a trade secret

SECTION 4. FIRST AID MEASURES

General advice	: Move out of dangerous area. Consult a physician. Show this material safety data sheet to the doctor in attendance.
If inhaled	: Move to fresh air. Consult a physician after significant exposure.
In case of skin contact	: Take off contaminated clothing and shoes immediately. Wash off with soap and plenty of water. If symptoms persist, call a physician.
In case of eye contact	: Remove contact lenses. Keep eye wide open while rinsing. If eye irritation persists, consult a specialist.
If swallowed	: Clean mouth with water and drink afterwards plenty of water. Do not induce vomiting without medical advice. Do not give milk or alcoholic beverages. Never give anything by mouth to an unconscious person. Obtain medical attention.
Most important symptoms and effects, both acute and delayed	: sensitizing effects Asthmatic appearance Respiratory disorder Allergic reactions Headache May cause an allergic skin reaction.



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

Harmful if inhaled.
May cause allergy or asthma symptoms or breathing difficulties if inhaled.

Notes to physician : Treat symptomatically.

SECTION 5. FIRE-FIGHTING MEASURES

- Suitable extinguishing media : Alcohol-resistant foam
Carbon dioxide (CO₂)
Dry chemical
- Unsuitable extinguishing media : Water
High volume water jet
- Specific hazards during fire fighting : Do not use a solid water stream as it may scatter and spread fire.
- Further information : Use water spray to cool unopened containers.
Collect contaminated fire extinguishing water separately. This must not be discharged into drains.
Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.
- Special protective equipment for fire-fighters : In the event of fire, wear self-contained breathing apparatus.

SECTION 6. ACCIDENTAL RELEASE MEASURES

- Personal precautions, protective equipment and emergency procedures : Use personal protective equipment.
Remove all sources of ignition.
Deny access to unprotected persons.
Beware of vapors accumulating to form explosive concentrations. Vapors can accumulate in low areas.
- Environmental precautions : Prevent product from entering drains.
If the product contaminates rivers and lakes or drains inform respective authorities.
Local authorities should be advised if significant spillages cannot be contained.
- Methods and materials for containment and cleaning up : Contain spillage, and then collect with non-combustible absorbent material, (e.g. sand, earth, diatomaceous earth, vermiculite) and place in container for disposal according to local / national regulations (see section 13).

SECTION 7. HANDLING AND STORAGE

- Advice on protection against : Use explosion-proof equipment.



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

fire and explosion	Keep away from heat/ sparks/ open flames/ hot surfaces. No smoking. Take precautionary measures against electrostatic discharges.
Advice on safe handling	: Avoid formation of aerosol. Do not breathe vapors or spray mist. Avoid exceeding the given occupational exposure limits (see section 8). Do not get in eyes, on skin, or on clothing. For personal protection see section 8. Persons with a history of skin sensitization problems or asthma, allergies, chronic or recurrent respiratory disease should not be employed in any process in which this mixture is being used. Smoking, eating and drinking should be prohibited in the application area. Take precautionary measures against static discharge. Provide sufficient air exchange and/or exhaust in work rooms. Open drum carefully as content may be under pressure. Take necessary action to avoid static electricity discharge (which might cause ignition of organic vapors). Follow standard hygiene measures when handling chemical products.
Conditions for safe storage	: Store in original container. Keep in a well-ventilated place. Containers which are opened must be carefully resealed and kept upright to prevent leakage. Observe label precautions. Store in accordance with local regulations.
Materials to avoid	: Explosives Oxidizing agents Poisonous gases Poisonous liquids

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Ingredients with workplace control parameters

Components	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
solvent naphtha (petroleum), light arom.	64742-95-6	TWA	500 ppm 2,000 mg/m ³	OSHA Z-1
		TWA	400 ppm 1,600 mg/m ³	OSHA P0
hexamethylene-di-isocyanate	822-06-0	TWA	0.005 ppm	ACGIH

The above constituents are the only constituents of the product which have a PEL, TLV or other rec-



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

ommended exposure limit. At this time, the other constituents have no known exposure limits.

Engineering measures : Use of adequate ventilation should be sufficient to control worker exposure to airborne contaminants. If the use of this product generates dust, fumes, gas, vapor or mist, use process enclosures, local exhaust ventilation or other engineering controls to keep worker exposure below any recommended or statutory limits.
The engineering controls also need to keep gas, vapor or dust concentrations below any lower explosive limits.

Personal protective equipment

Respiratory protection : Use a properly fitted NIOSH approved air-purifying or air-fed respirator complying with an approved standard if a risk assessment indicates this is necessary.

The filter class for the respirator must be suitable for the maximum expected contaminant concentration (gas/vapor/aerosol/particulates) that may arise when handling the product. If this concentration is exceeded, self-contained breathing apparatus must be used.

Hand protection : Chemical-resistant, impervious gloves complying with an approved standard should be worn at all times when handling chemical products if a risk assessment indicates this is necessary.

Eye protection : Safety eyewear complying with an approved standard should be used when a risk assessment indicates this is necessary.

Skin and body protection : Choose body protection in relation to its type, to the concentration and amount of dangerous substances, and to the specific work-place.

Hygiene measures : Avoid contact with skin, eyes and clothing.
Wash hands before breaks and immediately after handling the product.
Remove respiratory and skin/eye protection only after vapors have been cleared from the area.
Remove contaminated clothing and protective equipment before entering eating areas.
Wash thoroughly after handling.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance : liquid
Color : amber
Odor : characteristic



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

Odor Threshold	:	No data available
pH	:	Not applicable
Melting point/range / Freezing point	:	No data available
Boiling point/boiling range	:	No data available
Flash point	:	115 °F / 46 °C (Method: closed cup)
Evaporation rate	:	No data available
Flammability (solid, gas)	:	No data available
Upper explosion limit / Upper flammability limit	:	No data available
Lower explosion limit / Lower flammability limit	:	No data available
Vapor pressure	:	0.01 hpa
Relative vapor density	:	No data available
Density	:	ca. 1.1 g/cm ³ (73 °F / 23 °C)
Solubility(ies)		
Water solubility	:	insoluble
Solubility in other solvents	:	No data available
Partition coefficient: n-octanol/water	:	No data available
Autoignition temperature	:	No data available
Decomposition temperature	:	No data available
Viscosity		
Viscosity, dynamic	:	No data available
Viscosity, kinematic	:	> 20.5 mm ² /s (104 °F / 40 °C)
Explosive properties	:	No data available
Oxidizing properties	:	No data available
Volatile organic compounds (VOC) content	:	279 g/l A+B Combined. With exempt solvent.
		282 g/l Sikafloor®-340 Part A + B + Sikafloor®-372 Urethane Accel-



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

erator Combined. With exempt solvent.

SECTION 10. STABILITY AND REACTIVITY

Reactivity	: No dangerous reaction known under conditions of normal use.
Chemical stability	: The product is chemically stable.
Possibility of hazardous reactions	: Stable under recommended storage conditions. Vapors may form explosive mixture with air.
Conditions to avoid	: Heat, flames and sparks.
Incompatible materials	: No data available
Hazardous decomposition products	: No decomposition if stored and applied as directed.

SECTION 11. TOXICOLOGICAL INFORMATION

Acute toxicity

Harmful if inhaled.

Components:

hexamethylene-di-isocyanate:

Acute oral toxicity	: LD50 Oral (Rat): 746 mg/kg
Acute inhalation toxicity	: LC50 (Rat): 0.124 mg/l Exposure time: 4 h Test atmosphere: vapor
Acute dermal toxicity	: LD50 Dermal (Rat): > 7,000 mg/kg

Skin corrosion/irritation

Not classified due to lack of data.

Serious eye damage/eye irritation

Not classified due to lack of data.

Respiratory or skin sensitization

Skin sensitization

May cause an allergic skin reaction.

Respiratory sensitization

May cause allergy or asthma symptoms or breathing difficulties if inhaled.

Germ cell mutagenicity

Not classified due to lack of data.



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

Carcinogenicity

Not classified due to lack of data.

IARC Not applicable

OSHA Not applicable

NTP Not applicable

Reproductive toxicity

Not classified due to lack of data.

STOT-single exposure

Not classified due to lack of data.

STOT-repeated exposure

Not classified due to lack of data.

Once sensitized, a severe allergic reaction may occur when subsequently exposed to very low levels.

Aspiration toxicity

Not classified due to lack of data.

SECTION 12. ECOLOGICAL INFORMATION

Ecotoxicity

No data available

Persistence and degradability

No data available

Bioaccumulative potential

No data available

Mobility in soil

No data available

Other adverse effects

Product:

Additional ecological information : Do not empty into drains; dispose of this material and its container in a safe way.
Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.

SECTION 13. DISPOSAL CONSIDERATIONS

Disposal methods

Waste from residues : Disposal of this product, solutions and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements.



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

Contaminated packaging : Empty containers should be taken to an approved waste handling site for recycling or disposal.

SECTION 14. TRANSPORT INFORMATION

International Regulations

IATA-DGR

UN/ID No. : UN 1263
Proper shipping name : Paint
Class : 3
Packing group : III
Labels : Flammable Liquids
Packing instruction (cargo aircraft) : 366
Packing instruction (passenger aircraft) : 355

IMDG-Code

UN number : UN 1263
Proper shipping name : PAINT
Class : 3
Packing group : III
Labels : 3
EmS Code : F-E, S-E
Marine pollutant : no

Domestic regulation

49 CFR

UN/ID/NA number : UN 1263
Proper shipping name : Paint
Class : 3
Packing group : III
Labels : FLAMMABLE LIQUID
ERG Code : 128
Marine pollutant : no

DOT: As per 49CFR 173.150 (f) Combustible Liquid Exception, Material is Not Regulated.

IMDG: For Limited Quantity special provisions reference IMDG Code Chapter 3.4

Special precautions for user

The transport classification(s) provided herein are for informational purposes only, and solely based upon the properties of the unpackaged material as it is described within this Safety Data Sheet. Transportation classifications may vary by mode of transportation, package sizes, and variations in regional or country regulations.

SECTION 15. REGULATORY INFORMATION

TSCA list : All chemical substances in this product are either listed as active on the TSCA Inventory or are in compliance with a TSCA



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

Inventory exemption.

No substances are subject to a Significant New Use Rule.

No substances are subject to TSCA 12(b) export notification requirements.

CERCLA Reportable Quantity

Components	CAS-No.	Component RQ (lbs)
hexamethylene-di-isocyanate	822-06-0	100

SARA 304 Extremely Hazardous Substances Reportable Quantity

This material does not contain any components with a section 304 EHS RQ.

SARA 302 Extremely Hazardous Substances Threshold Planning Quantity

This material does not contain any components with a section 302 EHS TPQ.

SARA 311/312 Hazards : Flammable (gases, aerosols, liquids, or solids)
Acute toxicity (any route of exposure)
Respiratory or skin sensitization

SARA 313 : This material does not contain any chemical components with known CAS numbers that exceed the threshold (De Minimis) reporting levels established by SARA Title III, Section 313.

Clean Air Act

This product does not contain any hazardous air pollutants (HAP), as defined by the U.S. Clean Air Act Section 112 (40 CFR 61).

California Prop. 65

 **WARNING:** This product can expose you to chemicals including cumene, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov.

SECTION 16. OTHER INFORMATION

Full text of other abbreviations

ACGIH : USA. ACGIH Threshold Limit Values (TLV)
OSHA P0 : USA. Table Z-1-A Limits for Air Contaminants (1989 vacated values)
OSHA Z-1 : USA. Occupational Exposure Limits (OSHA) - Table Z-1 Limits for Air Contaminants
ACGIH / TWA : 8-hour, time-weighted average
OSHA P0 / TWA : 8-hour time weighted average
OSHA Z-1 / TWA : 8-hour time weighted average

Notes to Reader

The information contained in this Safety Data Sheet applies only to the actual Sika Corporation ("Sika") product identified and described herein. This information is not intended to address, nor



Sikafloor® 340 Part B

Revision Date 11/09/2023

Print Date 11/09/2023

does it address the use or application of the identified Sika product in combination with any other material, product or process. All of the information set forth herein is based on technical data regarding the identified product that Sika believes to be reliable as of the date hereof. Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's current Product Data Sheet, product label and Safety Data Sheet for each Sika product, which are available at web site and/or telephone number listed in Section 1 of this SDS.

SIKA MAKES NO WARRANTIES EXPRESS OR IMPLIED AND ASSUMES NO LIABILITY ARISING FROM THIS INFORMATION OR ITS USE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES AND SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

All sales of Sika products are subject to its current terms and conditions of sale available at www.sikausa.com or 201-933-8800.

Revision Date 11/09/2023

000000604947
US / Z8

Sikafloor® Urethane Color Additive (all colors)

Revision Date 06/15/2018

Print Date 06/15/2018

1. Identification

Product name : Sikafloor® Urethane Color Additive (all colors)

Supplier : Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
USA
www.sikausa.com

Telephone : (201) 933-8800

Telefax : (201) 804-1076

E-mail address : ehs@sika-corp.com

Emergency telephone : CHEMTREC: 800-424-9300
INTERNATIONAL: 703-527-3887

Recommended use of the chemical and restrictions on use : For further information, refer to product data sheet.

2. Hazards identification**GHS Classification**

Not a hazardous substance or mixture.

GHS label elements

Not a hazardous substance or mixture.

Warning : Reports have associated repeated and prolonged exposure to some of the chemicals in this product with permanent brain, liver, kidney and nervous system damage. Intentional misuse by deliberate concentration and inhalation of vapors may be harmful or fatal.

See Section 11 for more detailed information on health effects and symptoms.

There are no hazards not otherwise classified that have been identified during the classification process.

There are no ingredients with unknown acute toxicity used in a mixture at a concentration $\geq 1\%$.

3. Composition/information on ingredients**Hazardous ingredients**

Chemical name	CAS-No.	Concentration (%)
---------------	---------	-------------------



n-butyl acetate	123-86-4	>= 2 - < 5 %
2-methoxy-1-methylethyl acetate	108-65-6	>= 2 - < 5 %
Dipropyleneglycol methylether	34590-94-8	>= 2 - < 5 %

* All of the hazardous ingredients above apply only to the black and RAL 6001 emerald green colors. '2-methoxy-1-methylethyl acetate' is present in the RAL 3020, RAL 1018, tile red, safety blue 450, tan 251, and highgate green colors.

There are no additional ingredients present which, within the current knowledge of the supplier and in the concentrations applicable, are classified as hazardous to health or the environment and hence require reporting in this section.

4. First aid measures

If inhaled	: Move to fresh air.
In case of skin contact	: Take off contaminated clothing and shoes immediately. Wash off with soap and plenty of water.
In case of eye contact	: Flush eyes with water as a precaution. Remove contact lenses. Keep eye wide open while rinsing.
If swallowed	: Clean mouth with water and drink afterwards plenty of water. Do not induce vomiting without medical advice. Do not give milk or alcoholic beverages. Never give anything by mouth to an unconscious person.
Most important symptoms and effects, both acute and delayed	: No known significant effects or hazards. See Section 11 for more detailed information on health effects and symptoms.
Protection of first-aiders	: No hazards which require special first aid measures.
Notes to physician	: Treat symptomatically.

5. Fire-fighting measures

Suitable extinguishing media	: Use extinguishing measures that are appropriate to local circumstances and the surrounding environment.
Specific extinguishing methods	: Collect contaminated fire extinguishing water separately. This must not be discharged into drains. Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.
Special protective equipment for fire-fighters	: In the event of fire, wear self-contained breathing apparatus.

6. Accidental release measures

Environmental precautions	: Local authorities should be advised if significant spillages
---------------------------	--



cannot be contained.

Methods and materials for containment and cleaning up : Wipe up with absorbent material (e.g. cloth, fleece).
Keep in suitable, closed containers for disposal.

7. Handling and storage

Advice on safe handling : For personal protection see section 8.
No special handling advice required.
Follow standard hygiene measures when handling chemical products.

Conditions for safe storage : Keep container tightly closed in a dry and well-ventilated place.
Store in accordance with local regulations.

Materials to avoid : No data available

8. Exposure controls/personal protection

Component	CAS-No.	Basis **	Value	Exposure limit(s)* / Form of exposure
n-butyl acetate	123-86-4	OSHA Z-1	TWA	150 ppm 710 mg/m3
		OSHA P0	TWA	150 ppm 710 mg/m3
		OSHA P0	STEL	200 ppm 950 mg/m3
		ACGIH	TWA	50 ppm
		ACGIH	STEL	150 ppm
Dipropyleneglycol methylether	34590-94-8	ACGIH	TWA	100 ppm
		ACGIH	STEL	150 ppm
		OSHA Z-1	TWA	100 ppm 600 mg/m3
		OSHA P0	TWA	100 ppm 600 mg/m3
		OSHA P0	STEL	150 ppm 900 mg/m3



*The above mentioned values are in accordance with the legislation in effect at the date of the release of this safety data sheet.

****Basis**

ACGIH. Threshold Limit Values (TLV)

OSHA P0. Table Z-1, Limit for Air Contaminant (1989 Vacated Values)

OSHA P1. Permissible Exposure Limits (PEL), Table Z-1, Limit for Air Contaminant

OSHA P2. Permissible Exposure Limits (PEL), Table Z-2

OSHA Z3. Table Z-3, Mineral Dust

Engineering measures : Use of adequate ventilation should be sufficient to control worker exposure to airborne contaminants. If the use of this product generates dust, fumes, gas, vapor or mist, use process enclosures, local exhaust ventilation or other engineering controls to keep worker exposure below any recommended or statutory limits.

Personal protective equipment

Respiratory protection : Use a properly fitted NIOSH approved air-purifying or air-fed respirator complying with an approved standard if a risk assessment indicates this is necessary.

The filter class for the respirator must be suitable for the maximum expected contaminant concentration (gas/vapor/aerosol/particulates) that may arise when handling the product. If this concentration is exceeded, self-contained breathing apparatus must be used.

Hand protection

Remarks : Chemical-resistant, impervious gloves complying with an approved standard should be worn at all times when handling chemical products if a risk assessment indicates this is necessary.

Eye protection : Safety eyewear complying with an approved standard should be used when a risk assessment indicates this is necessary.

Skin and body protection : Choose body protection in relation to its type, to the concentration and amount of dangerous substances, and to the specific work-place.

Hygiene measures : Wash hands before breaks and immediately after handling the product.
Remove contaminated clothing and protective equipment before entering eating areas.

9. Physical and chemical properties

Appearance : paste

Color : various



Odor	: slight
Odor Threshold	: No data available
Flash point	: 223 °F (106 °C)
Ignition temperature	: No data available
Decomposition temperature	: No data available
Lower explosion limit (Vol%)	: No data available
Upper explosion limit (Vol%)	: No data available
Flammability (solid, gas)	: No data available
Oxidizing properties	: No data available
pH	: No data available
Melting point/range / Freezing point	: No data available
Boiling point/boiling range	: No data available
Vapor pressure	: 0.01 mmHg (0.01 hpa)
Density	: 1.145 – 1.942 g/cm3
Water solubility	: Note: insoluble
Partition coefficient: n- octanol/water	: No data available
Viscosity, dynamic	: No data available
Viscosity, kinematic	: > 20.5 mm2/s
Relative vapor density	: No data available
Evaporation rate	: No data available
Burning rate	: No data available
Volatile organic compounds (VOC) content	: 49 g/l black color : 75 g/l all other colors

10. Stability and reactivity

Reactivity	: No dangerous reaction known under conditions of normal use.
Chemical stability	: The product is chemically stable.
Possibility of hazardous reactions	: Stable under recommended storage conditions.



Conditions to avoid : No data available

Incompatible materials : No data available

11. Toxicological information

Acute toxicity

Not classified based on available information.

Ingredients:

n-butyl acetate:

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

Acute inhalation toxicity : LC50 (Rat): 23.4 mg/l
Exposure time: 4 h
Test atmosphere: vapor

Acute dermal toxicity : LD50 Dermal (Rabbit): > 5,000 mg/kg

2-methoxy-1-methylethyl acetate:

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

Acute dermal toxicity : LD50 Dermal (Rabbit): > 5,000 mg/kg

Dipropyleneglycol methylether:

Acute oral toxicity : LD50 Oral (Rat): > 5,000 mg/kg

Acute dermal toxicity : LD50 Dermal (Rabbit): > 5,000 mg/kg

Skin corrosion/irritation

Not classified based on available information.

Serious eye damage/eye irritation

Not classified based on available information.

Respiratory or skin sensitization

Skin sensitization: Not classified based on available information.

Respiratory sensitization: Not classified based on available information.

Germ cell mutagenicity

Not classified based on available information.

Reproductive toxicity

Not classified based on available information.

STOT-single exposure

Not classified based on available information.

STOT-repeated exposure

Reports have associated repeated and prolonged exposure to some of the chemicals in this product with permanent brain, liver, kidney and nervous system damage. Intentional misuse by deliberate concentration and inhalation of vapors may be harmful or fatal.

Aspiration toxicity

Not classified based on available information.

**Carcinogenicity**

Not classified based on available information.

IARC

Group 2B: Possibly carcinogenic to humans

titanium dioxide

13463-67-7 *applicable to all colors
except black

Carbon black

1333-86-4 *applicable to all colors except
RAL 3020, RAL 1018, safety blue 450, white,
beige 248, RAL 1015, RAL 9016, RAL 1013,
RAL 5015, safety yellow 684, RAL 6001**NTP**

Not applicable

Animal Toxicity:

Rat, oral, duration 2 year

Effect: no tumors

Mouse, oral, duration 2 years

Effect: no tumors

Mouse, dermal, duration 18 months

Effect: no skin tumors

Rat, inhalation, duration 2 years

Target organ: lungs

Effect: inflammation, fibrosis, tumors

Note: Tumors in the rat lung are considered to be related to the "particle overload phenomenon" rather than to a specific chemical effect of carbon black itself in the lung. These effects in rats have been reported in many studies on other poorly soluble inorganic particles and appear to be rat specific. Tumors have not been observed in other species (i.e., mouse and hamster) for carbon black or other poorly soluble particles under similar circumstances and study conditions.

Mortality studies (human data): A study on carbon black production workers in the UK (Sorahan, 2001) found an increased risk of lung cancer in two of the five plants studied; however, the increase was not related to the dose of carbon black. Thus, the authors did not consider the increased risk in lung cancer to be due to carbon black exposure. A German study of carbon black workers at one plant (Morfeld, 2006; Buechte, 2006) found a similar increase in lung cancer risk but, like the Sorahan, 2001 (UK study) found no association with carbon black exposure. A large US study of 18 plants showed a reduction in lung cancer risk in carbon black production workers (DEll, 2006). Based upon these studies, the February 2006 Working Group at the International Agency for Research on Cancer (IARC) concluded that the human evidence for carcinogenicity was inadequate (IARC, 2010).

Since the IARC evaluation of carbon black, Sorahan and Harrington (2007) have re-analyzed the UK study data using an alternative exposure hypothesis and found a positive association with carbon black exposure in two of the five plants. The same exposure hypothesis was applied by Morfeld and McCunney (2009) to the German cohort; in contrast, they found no association between carbon black exposure and lung cancer risk and, thus, no support for the alternative exposure hypothesis used by Sorahan and Harrington.

Overall, as a result of these detailed investigations, no causative link between carbon black



exposure and cancer risk in humans has been demonstrated.

IARC CANCER CLASSIFICATION: In 2006 IARC re-affirmed its 1995 finding that there is "inadequate evidence" from human health studies to assess whether carbon black causes cancer in humans. IARC concluded that there is "sufficient evidence" in experimental animal studies for the carcinogenicity of carbon black. IARC's overall evaluation is that carbon black is "possibly carcinogenic to humans" (Group 2B)". This conclusion was based on IARC's guidelines, which generally require such a classification if one species exhibits carcinogenicity in two or more animal studies (IARC, 2010).

Solvent extracts of carbon black were used in one study of rats in which skin tumors were found after dermal application and several studies of mice in which sarcomas were found following subcutaneous injection. IARC concluded that there was "sufficient evidence" that carbon black extracts can cause cancer in animals (Group 2B).

ICGIH CANCER CLASSIFICATION: Confirmed Animal Carcinogen with Unknown Relevance to Humans (Category A3 Carcinogen).

ASSESSMENT: Applying the guidelines of self-classification under the Globally Harmonized System of Classification and Labeling of Chemicals, carbon black is not classified as a carcinogen. Lung tumors are induced in rats as a result of repeated exposure to inert, poorly soluble particles like carbon black and other poorly soluble particles. Rats tumors are a result of a secondary non-genotoxic mechanism that has questionable relevance for classification in humans. In support of this opinion, the CLP Guidance for Specific Target Organ Toxicity - Repeated Exposure (STOT-RE), cites lung overload under mechanisms not relevant to humans. Human health studies show that exposure to carbon black does not increase the risk to carcinogenicity.

Titanium dioxide (13463-67-7)

In lifetime inhalation studies of rats, airborne respirable-size titanium dioxide particles have been shown to cause an increase in lung tumors at concentrations associated with substantial particle lung burdens and consequential pulmonary overload and inflammation. The potential for these adverse health effects appears to be closely related to the particle size and the amount of the exposed surface area that comes into contact with the lung. However, tests with other laboratory animals such as mice and hamsters, indicate that rats are significantly more susceptible to the pulmonary overload and inflammation that cause lung cancer. Epidemiology studies do not suggest an increased risk of cancer in humans from occupational exposure to titanium dioxide. Titanium dioxide has been characterized by IARC as possibly carcinogenic to humans (Group 2B) through inhalation (not ingestion). It has not been characterized as a potential carcinogen by either NTP or OSHA.

12. Ecological information

Other information

Do not empty into drains; dispose of this material and its container in a safe way.
Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains and sewers.

Component:

n-butyl acetate

123-86-4

Toxicity to algae:
EC50



Species: *Desmodesmus subspicatus* (green algae)
Dose: 647.7 mg/l
Exposure time: 72 h

13. Disposal considerations

Disposal methods

- | | | |
|------------------------|---|--|
| Waste from residues | : | Disposal of this product, solutions and any by-products should at all times comply with the requirements of environmental protection and waste disposal legislation and any regional local authority requirements. |
| Contaminated packaging | : | Empty containers should be taken to an approved waste handling site for recycling or disposal. |

14. Transport information

DOT

Not dangerous goods

IATA

Not dangerous goods

IMDG

Not dangerous goods

Special precautions for user

No data available

Transport in bulk according to Annex II of MARPOL 73/78 and the IBC Code

Not applicable

15. Regulatory information

- | | | |
|------------------|---|---|
| TSCA list | : | All chemical substances in this product are either listed on the TSCA Inventory or are in compliance with a TSCA Inventory exemption. |
|------------------|---|---|

EPCRA - Emergency Planning and Community Right-to-Know

CERCLA Reportable Quantity

This material does not contain any components with a CERCLA RQ.

SARA304 Reportable Quantity

This material does not contain any components with a section 304 EHS RQ.

- | | | |
|-----------------------------|---|-----------------|
| SARA 311/312 Hazards | : | No SARA Hazards |
|-----------------------------|---|-----------------|

Sikafloor® Urethane Color Additive (all colors)

Revision Date 06/15/2018

Print Date 06/15/2018

- SARA 302** : This material does not contain any components with a section 302 EHS TPQ.
- SARA 313** : The following components are subject to reporting levels established by SARA Title III, Section 313:
- | | | |
|---|------------|---------------|
| bismuth vanadium tetraoxide | 14059-33-7 | ≥ 20 - ≤ 40 % |
| <i>* Applies to RAL 1018 and safety yellow 684</i> | | |
| copper chlorophthalocyanine | 12239-87-1 | ≥ 1 - ≤ 2.5 % |
| <i>* Applies to tile red, safety blue 450, and RAL 5015</i> | | |
| aluminum chloride | 1344-28-1 | ≥ 1 - ≤ 2.5 % |
| <i>* Applies to tile red, safety blue 450, tan 251, highgate green, white, beige 248, RAL 1015, RAL 9016, RAL 1013, medium grey 124, RAL 7038, light grey 122, RAL 1001, RAL 1019, raffia beige, and RAL 5015</i> | | |

Clean Air Act**Ozone-Depletion Potential**

This product neither contains, nor was manufactured with a Class I or Class II ODS as defined by the U.S. Clean Air Act Section 602 (40 CFR 82, Subpt. A, App.A + B).

This product does not contain any hazardous air pollutants (HAP), as defined by the U.S. Clean Air Act Section 112 (40 CFR 61).

This product does not contain any chemicals listed under the U.S. Clean Air Act Section 112(r) for Accidental Release Prevention (40 CFR 68.130, Subpart F).

California Prop 65

WARNING: Cancer – www.P65Warnings.ca.gov

16. Other information**HMIS Classification**

Health	/	1
Flammability		1
Physical Hazard		0
Personal Protection		x

Caution: HMIS® rating is based on a 0-4 rating scale, with 0 representing minimal hazards or risks, and 4 representing significant hazards or risks. Although HMIS® rating is not required on SDSs under 29 CFR 1910.1200, the preparer may choose to provide them. HMIS® rating is to be used with a fully implemented HMIS® program. HMIS® is a registered mark of the National Paint & Coatings Association (NPCA). Please note HMIS® attempts to convey full health warning information to all employees.

Notes to Reader

The information contained in this Safety Data Sheet applies only to the actual Sika Corporation ("Sika") product identified and described herein. This information is not intended to address, nor does it address the use or application of the identified Sika product in combination with any other material, product or process. All of the information set forth herein is based on technical data regarding the identified product that Sika believes to be reliable as of the date hereof. Prior to each use of any Sika product, the user must always read and

Sikafloor® Urethane Color Additive (all colors)



Revision Date 06/15/2018

Print Date 06/15/2018

follow the warnings and instructions on the product's current Product Data Sheet, product label and Safety Data Sheet for each Sika product, which are available at web site and/or telephone number listed in Section 1 of this SDS.

SIKA MAKES NO WARRANTIES EXPRESS OR IMPLIED AND ASSUMES NO LIABILITY ARISING FROM THIS INFORMATION OR ITS USE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES AND SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

All sales of Sika products are subject to its current terms and conditions of sale available at www.sikausa.com or 201-933-8800.

Revision Date 06/15/2018

Material number: 403156